

**Dhr. Ron Verlouw
VESCOB BV
Postbus 70
NL-5753 AV DEURNE
NEDERLAND**

your delivery of
2011-02-18

your reference

our reference
WVW/1864

date
Zwijnaarde, 2011-02-22

Analysis Report 78625

Required tests :

Determination of the resistance to pilling - Martindale

Identification number	Information given by the client	Date of receipt
T101697	Samar	2011-02-16

Willy Vande Wiele
order responsible

For further information, please contact our sectorial adviser Daniel Verstraete

This report runs to 2 pages and may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.

our reference	date	page
WVW/1864	2011-02-22	2 / 2

Reference : T101697 - Samar

Determination of the resistance to pilling - Martindale

1. Method:

Applied standard : EN ISO 12945 part 2 (year: 2000)
on conditioned material (20°C and 65% rel. hum.)

Deviations of the standard : -

Pre-treatment : none

Apparatus : Nu-Martindale

Pressure on the specimen : 415g

Abradant : crossbred worsted spun, plain woven fabric

Number of specimens : 3

Number of assessors : 2

2. Results:

Date of ending the test: 21-02-2011

specimen	assessment after ... cycles:			
	500	1000	2 000	5 000
1	4-5	4	3-4	4
2	4-5	4	3-4	4
3	4-5	4	3-4	4

See tested specimens enclosed.