



Report Number: 18-006363 Revision Number:1 Date Order Received: 10/18/2018

For the Account of:

Raxon Fabrics 2289 Ross Mill Road Henderson, NC 37536

Client's Identification:

Rolla Test #698

CERTIFICATE OF TESTING

TEST PERFORMED: Colorfastness to Light AATCC Test Method 16.3-2014, Option 3

TEST RESULTS

Rating Class 4.0 Number of Hours 40

RATING SYSTEM

- Class 5 No fading or color change
- Class 4 Slight fading or color change
- Class 3 Noticeable fading or color change
- Class 2 Considerable fading or color change
- Class 1 Much fading or color change

NOTES

Light Source:XerScale Used for Evaluation:AA

Xenon -Arc, Water Cooled, Continuous Light AATCC Gray Scale for Color Change

ACCEPTANCE CRITERIA

A.C.T. Standard Upholstery Direct Glue Wallcoverings Panels and Upholstered Walls Drapery Acceptance Criteria Class 4 minimum - 40 hours Class 4 minimum - 40 hours Class 4 minimum - 40 hours Class 4 minimum - 60 hours

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver

Authorized Signature

Date Order Completed: 10/26/2018

553 76th Street, Byron Center, MI 49315

P: 616-559-6123 E: testlab@applied-textiles.com

Page 1 of 1

This laboratory test is not intended to reflect fabric performance under actual conditions. The certification procedure merely measures the performance of samples under the predetermined and specific test conditions prescribed by the standard specified. This certificate applies only to the standards or processing identified and to the random sample(s) tested. The test results are representative of the qualities of the piece or lot only to the standards or processing identified and to the random sample(s) tested. The test results are representative of the qualities of the piece or lot only to the standards or processing identified and to the random sample(s) tested. The test results are representative of the qualities of the piece or lot only to the standard specific test.

Our reports and letters are for the exclusive use of the customer to whom they are addressed and they and the corporation named on the reverse are not to be used under any circumstances without prior written approval. Samples will not be retained, unless specified by the customer. Retained samples will be kept a maximum time of one year unless a specific retention period is necessary.