



Vescom B.V. Sint Jozefstraat 20 NL-5753 AV Deurne Nederland

Your notice of 12-03-2020

Your reference

Date 28-04-2020

Analysis Report 20.01487.03

Required tests:

EN 13773 (2003)

Identification	Information given by the client	Date of receipt
number		
T2005624	Chira	12-03-2020

Gina Créelle Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.









Analysis Report 20.01487.03 Date 28-04-2020 Page 2/4

Reference: T2005624 - Chira

<u>Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.</u>

Date of ending the test 15-04-2020

Standard used EN 1101 (1995) + A1 (2005)

Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

Ignition Bottom edge

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

Flame application	Cases of	Cases of		
time (s)	ignition	non-ignition		
1	0	1		
2	0	1		
3	0	1		
4	0	1		
5	0	1		
10	0	1		
15	0	1		
20	0	5		

The mean of the recorded times at which ignition was observed is calculated No ignition within $20\ \mathrm{s}$







Width

Flame application	Cases of	Cases of		
time (s)	ignition	non-ignition		
1	0	1		
2	0	1		
3	0	1		
4	0	1		
5	0	1		
10	0	1		
15	0	1		
20	0	5		

The mean of the recorded times at which ignition was observed is calculated No ignition within 20 s





Analysis Report 20.01487.03 Date 28-04-2020 Page 4/4

Reference: T2005624 - Chira

Textiles and textile products - Burning behaviour - Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.

Date of ending the test 21-04-2020 Standard used EN 13772 (2011) Product standard EN 13773 (2003)

Deviation from the standard

Conditioning 20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

	Face A	Face B	Face A	Face A
Severance1st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	135	105	125	105
Flaming debris	no	no	no	no

Width

	Face A	Face B	Face A	Face A
Severance1st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	110	105	120	110
Flaming debris	no	no	no	no

Class 1

Classification in accordance with EN 13773