

Vescom B.V.  
Michel Lemmen  
St. Jozefstraat 20  
5750 AB Deurne

Hengelo (ov), 25-3-2020

|                       |                  |                |                                 |
|-----------------------|------------------|----------------|---------------------------------|
| <b>Test Specimen:</b> | <b>Specimen:</b> | <b>Colour:</b> | <b>Client reference number:</b> |
|                       | A.               | Beige/grey     | Furka Plus 7064.19              |

|                     |                     |                           |
|---------------------|---------------------|---------------------------|
| <b>Examination:</b> | <b>Test number:</b> | <b>Test Name:</b>         |
|                     | 1.                  | Flex cracking resistance. |

**Results** See following pages

  
Laboratory Quality Control

This report consists of 2 numbered page(s) and can only be reproduced entirely. All services provided by Textile Lab are subjected to our current Terms and Conditions. The test result relates only to the tested item. Specimens were delivered by client. The interpretation of results and recommendations are for risk of the client and her reader. Regarding to this report Textile Lab does not accept responsibility for any damage caused due to the test results or services. The examined specimens are claimable at the office of Textile Lab within one month after the above-mentioned date. With the exception; when tested for fire/smoke properties, when returned to client or when the material has been consumed. No part of this report may be altered or published, without the prior written permission of the board of directors.

*Check this report of 25-3-2020 on authenticity. Page: 1 / 2*

**Testing • Research • Consulting**

**Test** : 1. Flex cracking resistance.  
**Norm** : EN DIN ISO 7854:1997-04  
**Methode** : Methode B (schildknecht method)  
**Cycles** : 400.000

| Results test 1 specimen:       | A.                  |
|--------------------------------|---------------------|
| Assessment of flex resistance. | 1 (slight crumpled) |
| Depth of cracking.             | 0(no cracking)      |

Original Report

  
Laboratory Quality Control

This report exists of 2 numbered page(s) and can only be reproduced entirely. All services provided by Textile Lab are subjected to our current Terms and Conditions. The test result relates only to the tested item. Specimens where delivered by client. The interpretation of results and recommendations are for risk of the client and her reader. Regarding to this report Textile Lab does not accept responsibility for any damage caused due to the test results or services. The examined specimens are claimable at the office of Textile Lab within one month after the above-mentioned date. With the exception; when tested for fire/smoke properties, when returned to client or when the material has been consumed. No part of this report may be altered or published, without the prior written permission of the board of directors.

*Check this report of 25-3-2020 on authenticity. Page: 2 / 2*

**Testing • Research • Consulting**