



Vescom BV
Sint-Jozefstraat 20
5753 AV Deurne
Nederland

Your notice of
27-01-2021

Your reference

Date
04-03-2021

Analysis Report 21.00560.01

Required tests :

EN 13773 (2003)

Sample id	Information given by the client	Date of receipt
T2101866	Bedra - 100% PES-FR	27-01-2021



Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

Reference: T2101866 - Bedra - 100% PES-FR

Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.

Date of ending the test 24-02-2021
 Standard used EN 1101 (1995) + A1 (2005)
 Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%


Ignition Bottom edge

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated
 No ignition within 20 s



Width

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated
No ignition within 20 s

Reference: T2101866 - Bedra - 100% PES-FR

Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.

Date of ending the test 03-03-2021
Standard used EN 13772 (2011)
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

	Face A	Face B	Face B	Face B
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	125	125	130	125
Flaming debris	no	no	no	no

Width

	Face A	Face B	Face B	Face B
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	125	130	125	130
Flaming debris	no	no	no	no

Classification in accordance with EN 13773 Class 1