

Vescom bv
Sint-Jozefstraat 20
5753 AV Deurne
NEDERLAND



Your notice of
07-03-2018

Your reference

Date
30-03-2018

Analysis Report 18.01439.02

Required tests :

**IMO - 2010 FTP Code Annex 1 - Fire tests - Test for upholstered furniture - smouldering
Fire test procedures - Part 8 cigarette test**
**IMO - 2010 FTP Code Annex 1 - Fire tests - Test for upholstered furniture - Match flame
Fire test procedures - Part 8 equivalent**

Identification number	Information given by the client	Date of receipt
T1805567	Noss 7058 100% PES	07-03-2018

Gina Créelle

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be

Inrichting erkend bij toepassing van de besluitwet van 30-01-1947 • Établissement reconnu par application de l'arrêté-loi du 30-01-1947
GENT • Technologiepark 7 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be
GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be
KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 281828 • fax +32 56 281830 • info@vkc.be
VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB

Reference: T1805567 - Noss 7058 100% PES

IMO upholstered furniture

Information given by the client

Type of furniture

Upholstery

Fabric

Composition

100% PES

Structure

Weave

Number of threads - warp

8.5/cm

Number of threads - weft

13.5/cm

Yarn count - warp

Nm 3.2

Yarn count - weft

Nm 3.2 + Nm 3.6 + Nm 20/2

Thickness in mm

1.5

Weight per unit area

655 g/m²

Colour

Grey

Inherently FR treated

yes

Reference: T1805567 - Noss 7058 100% PES

Fire tests - Test for upholstered furniture - smouldering cigarette test

Date of ending the test 28-03-2018
Standard used IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8
Deviation from the standard -
Conditioning 23°C, relative humidity 50%

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Filling SB 36140 (Recticel) - fire retardant foam - $\pm 36 \text{ kg/m}^3$

Ignition source: smouldering cigarette with the following specifications

Length: $(70 \pm 4) \text{ mm}$

Diameter: $(8.0 \pm 0.5) \text{ mm}$

Mass: $(0.95 \pm 0.15) \text{ mm}$

Smouldering rate: $(11.0 \pm 4.0) \text{ min} / 50 \text{ mm}$

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Smoulders more than 1 hour	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Occurrence of flames	no	no
	non-ignition	non-ignition

Conclusion Pass

Reference: T1805567 - Noss 7058 100% PES

Fire tests - Test for upholstered furniture - Match flame equivalent

Date of ending the test 28-03-2018
Standard used IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8

Deviation from the standard -

Conditioning 23°C, relative humidity 50%

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Filling SB 36140 (Recticel) - fire retardant foam - \pm 36 kg/m³

Flame application time (s) 20

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke/heat/glowing more than 120 s	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Flaming > 120 s	no	no
Afterflame time (s)	0	0
	non-ignition	non-ignition

Conclusion Pass