



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

April 24, 2017

VESCOM, B.V.
Sint Jozestraat 20
5753 Av Duerne

Reference: Laboratory Test Report
Lab Identification No. 24803
Invoice No. 55985

Dear Sir or Madam:

One (1) fabric sample, identified as **CHIRA TEST # 455 SILVER**, was received and tested in accordance with the test procedures outlined. The results are as follows:

Test Procedures

Test Results

| | <u>Warp</u> | <u>Fill</u> |
|---|-------------|--------------------|
| Yarn Slippage (lbf) ASTM D 434-95 | 31.0 | 23.5 |
| Colorfastness to Crocking AATCC 8-2013 | | Dry – 5 Wet – 5 |
| Colorfastness to Light (60 hrs) AATCC 16.3-2014 | | Grade 4-5 |

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

