



DIVERSIFIED
TESTING LABORATORIES, INC.
 WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
 P.O. BOX 4004
 BURLINGTON, NORTH CAROLINA 27215
 PHONE (336) 227-7710 • FAX (336) 227-1175
 www.diversifiedtestinglabs.com

April 24, 2017

VESCOM, B.V.
 Sint Jozestraat 20
 5753 Av Duerne

Reference: Laboratory Test Report
 Lab Identification No. 24803
 Invoice No. 55985

Dear Sir or Madam:

One (1) fabric sample, identified as **CHIRA TEST # 455**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2015 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Test Results</u>	
	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	29.96
2	0.0	22.01
3	0.0	27.17
4	0.0	25.95
5	0.0	20.97
6	0.0	21.05
7	0.0	24.44
8	0.0	23.19
9	0.0	24.44
<u>10</u>	<u>0.0</u>	<u>15.30</u>
AVG	0.0	23.45

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

