



Report Number: 17-003425

Revision Number:1

Date Order Received: 09/01/2017

For the Account of:

Vescom BV Sint Jozefstraat 20 NL-5753 AV Deurne

Client's Identification:	Bedra Print 8061

## **CERTIFICATE OF TESTING**

TEST PERFORMED: NFPA 701 Standard Methods of Fire Test for Flame Propagation of Textiles and Films 2015 – Test #1

## **TEST RESULTS**

Specimen	Mass Initial (g)	Mass Final (g)	Mass Loss (%)	Drip Burn (s)	Afterflame (s)
1	16.8	14.8	12	0.0	0.0
2	16.3	12.8	21	0.0	0.0
3	16.6	11.4	31	0.0	0.0
4	16.5	12.8	22	0.0	0.0
5	16.4	13.5	18	0.0	0.0
6	16.5	12.4	25	0.0	0.0
7	16.1	12.4	23	0.0	0.0
8	16.0	13.7	14	0.0	0.0
9	16.0	12.2	24	0.0	0.0
10	16.1	13.2	18	0.0	0.0
Average	16.3	12.9	21	0.0	0.0

Approximate weight (or	z./sq. yd): 8.0	Standard Deviation: 5.6	Average + 3 SD: 37.8
Product Configuration: Conditioning: ntended End-use (if kn	_ ,	☐ Multi Layer for minimum 30 minutes orapery	☐ 70 ±2°F & 65 ±2%RH for minimum 24 hours
<ol> <li>Where fragme seconds per seconds per seconds per seconds per seconds.</li> <li>Where the average seconds.</li> <li>Where the specific seconds.</li> </ol>	be recorded; however, it is not ents or residues of specimens of specimens of the sample of 10 specimens will be listed as a failurecimens do not demonstrate p	specimens, the material shall be r ecimens in a sample is greater tha re if it exceeds mean + 3 SD	iteria Imber continue to burn for more than an average of 2 Irecorded as failing. (Flaming Drip) In 40 percent, the material shall be recorded as failing. Ither of the conditions indicated above, the material shall
X	ed on the above Results and A Complies Does Not Comply	Acceptance Criteria, the item teste	ed:
pecified by the standar		obtained after testing specimen in	accordance with the procedures and equipment
Berta Stiven			

553 76th Street, Byron Center, MI 49315

**Authorized Signature** 

P: 616-559-6123 E: testlab@applied-textiles.com

Page 1 of 1

Date Order Completed: 09/18/2017