



Vescom bv
Sint-Jozefstraat 20
5753 AV DEURNE
Nederland

Your notice of
04-05-2017

Your reference

Date
22-09-2021

Analysis Report 17.02718.08

Required tests :
BS 5852 (2006)

**Clause 11 (upholstery composite) - Assessment of the
ignitability of upholstered seating - crib ignition source no. 5**

Sample id	Information given by the client	Date of receipt
T1709895	Eliot 7046 100% PES (PES-FR), 539 g/m ²	04-05-2017

Mike De Vrieze
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

Reference: T1709895 - Eliot 7046 100% PES (PES-FR), 539 g/m²

Clause 11 (upholstery composite) - Assessment of the ignitability of upholstered seating - crib ignition source no. 5

Date of ending the test 06-06-2017
Standard used BS 5852 (2006)
Deviation from the standard -
Conditioning 23°C, relative humidity 50%

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Water soaking of the cover No
Filling C55120 (Recticel) * - fire retardant foam - ± 60 kg/m³

* The filling complies with schedule 1 part 1 of the UK Furniture and Furnishings (Fire) (Safety) Regulations 1988

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Smoke, heat or glowing more than 1 hour	no	no
Smoulders more than 100 mm from source	no	no
Flaming criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Flames to extremities	no	no
Flames through thickness	no	no
Flame time >10 min	no	no
Flame time	4 min 51 s	3 min 38 s
	non-ignition - NI/5	non-ignition - NI/5

Conclusion Non-ignition - NI/5