

For the Account of:

Vescom, B.V. Sint Jozestraat 20 5753 Av Duerne

Client's Identification:

Foster

CERTIFICATE OF TESTING

TEST PERFORMED: Breaking Strength and Elongation of Textile Fabrics (Grab Test) ASTM D5034(G-E)

TEST RESULTS

		Specimen	Breaking Force
			lbf
W	arp	1	263
		2	265
		3	247
		4	271
		5	269
		Average	263
Fi	1	1	262
		2	232
		3	243
		4	233
		5	248
		6	216
		7	223
		8	218
		Average	234
6			
nent Used:	Tinius O	Tinius Olson H5KT Universal Testing Mach	

NO	TES
-	

Equipment Used:	Tinius Olson H5KT Universal Testing Machine
Load Cell Maximum:	1000 pounds
Jaw Size:	1 inch x 1 inch (face and back), rubber coated
Test Conditions:	70 ±4°F, 65 ±5% Relative Humidity
Sampling Method:	As Received

ACCEPTANCE CRITERIA

A.C.T. Standard	Acceptance Criteria
Upholstery	50 pounds minimum
Panels and Upholstered Walls	35 pounds minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Matrie illin Jillian Matice

Authorized Signature

Date Order Completed: 11/11/2021

553 76th Street, Byron Center, MI 49315 P: 616

P: 616-559-6123 E: testlab@applied-lab.com

Page 1 of 1

This laboratory test is not intended to reflect fabric performance under actual conditions. The certification procedure merely measures the performance of samples as received under the predetermined and specific test conditions prescribed by the stand specified. This certificate applies only to the standards or processing identified and to the random sample(s) tested. The test results are representative of the qualities of the piece or lot only to the standards or processing identified and to the random sample(s) tested. The test results are representative of the qualities of the piece or lot only to the extent the sample tested is representative of the piece or lot.

Our reports and letters are for the exclusive use of the customer to whom they are addressed and they and the corporation named on the reverse are not to be used under any circumstances without prior written approval. Samples will not be retained, unl specified by the customer. Retained samples will be kept a maximum time of one year unless a specific retention period is necessary.



Date of Issue: 12/2/2021 Report Number: 21-006018 Revision Number:2 Date Order Received: 11/10/2021