## applied lab



Date of Issue: 12/7/2022 Report Number: 22-003882 **Revision Number:1** Date Order Received: 11/22/2022

For the Account of:

Vescom, B.V. Sint Jozestraat 20 5750 AB Deurne Netherland

Client's Identification:

## Ponza

## **CERTIFICATE OF TESTING**

TEST PERFORMED: Abrasion Resistance of Textile Fabrics (Oscillatory Cylinder Method) ASTM D4157-13(2017); CFFA-1 ( a) Abrasion Resistance

**TEST RESULTS** 

N	lumber of Double Rubs	Warp (Length) Specimens	Fill (Width) Specimens
Specimen #1 Specimen #2 Severe Crocking	100,000 100,000	Slight wear Slight wear	Moderate wear Moderate wear
INTERPRETATION USED			
□ Option 1	The end point is reached on a woven fabric when two or more yarns have broken or on a knitted fabric, when a hole appears.		
X Option 2	The end point is reached when there is a change in shade or appearance that is sufficient to cause a customer to complain.		
NOTES			
Abradant Used: Samples Backed with			
Masking Tape:	🗆 Yes 🛛 No		
Tension:	4 pounds		
Compression:	3 pounds		
ACCEPTANCE CRITERIA			
A.C.T. Standard	Acceptance Criter		
General Contract Upho	, , , , , , , , , , , , , , , , , , , ,	akage or wear after 15,000 double rubs	
Heavy Duty Upholstery No appreciable breakage or wear after 30,000 double rubs			
	ION Based on the above Results and the A.C.T. Standard, the item tested: □ Unrated □ General Contract Upholstery ⊠ Heavy Duty Upholstery		

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver

Authorized Signature

Date Order Completed: 12/05/2022

553 76th Street, Byron Center, MI 49315 P: 616-559-6123 E: testlab@applied-lab.com

Page 1 of 1 This laboratory test is not intended to reflect fabric performance under actual conditions. The certification procedure merely measures the performance of samples as received under the predetermined and specific test conditions specified. This certificate applies only to the standards or processing identified and to the random sample(s) tested. The test results are representative of the qualities of the piece or lot only to the extent the sample tested is representative of the piece or lot. rescribed by the standard

Our reports and letters are for the exclusive use of the customer to whom they are addressed and they and the corporation named on the reverse are not to be used under any circumstances without prior written approval. Samples will not be retained. unless specified by the customer. Retained samples will be kept a maximum time of one year unless a specific retention period is necessary.