

CLASSIFICATION OF REACTION TO FIRE PERFORMANCE IN ACCORDANCE WITH EN 13501-1:2018

Classification no.	2023-Efectis-R000709
Sponsor	Vescom B.V. Sint Jozefstraat 20 5753 AV DEURNE THE NETHERLANDS
Product name	Vinyl Wallcovering 350 g/m²
Prepared by	Efectis Nederland BV
Notified body no.	1234
Author(s)	D. van Dijk B.Eng. A. González Santamaría M.Sc. A.H.L.M. Zwinkels B.Sc.
Project number	ENL-23-000495
Date of issue	August 2023
Number of pages	5

1. INTRODUCTION

This classification report defines the classification assigned to **Vinyl Wallcovering 350 g/m²** in accordance with the procedures given in EN 13501-1:2018.

2. DETAILS OF CLASSIFIED PRODUCT

2.1 GENERAL

The product, **Vinyl Wallcovering 350 g/m²**, is defined as a wall covering.

2.2 MANUFACTURER/IMPORTER

Vescom B.V.
Sint Jozefstraat 20
5753 AV DEURNE
THE NETHERLANDS

2.3 PRODUCT DESCRIPTION

According to the sponsor the product is composed of:

- vinyl wallcovering with a thickness of 0.20 mm and with a mass per unit area (surface density) of 310 g/m²;
- woven cotton backing with a thickness of 0.25 mm and a surface density of 40 g/m²;
- glued with Vescom 3000 wallcovering paste with a surface density of 300 g/m² (wet and liquid form before application);
- Colour white.

The product has a total thickness of 0.45 mm, a density of approx. 778 kg/m³ and a surface density of 0.350 kg/m². Including (dry) adhesive the surface density is approx. 0.430 kg/m².

3. STANDARDS, REPORTS, RESULTS AND CRITERIA IN SUPPORT OF THIS CLASSIFICATION

3.1 APPLICABLE (PRODUCT) STANDARDS

EN ISO 11925-2:2020	Reaction to fire tests - Ignitability of products subjected to direct impingement of flame - Part 2: Single-flame source test
EN 13823:2020	Reaction to fire tests for building products - Building products, excluding floorings exposed to the thermal attack by a single burning item
EN 13238:2010	Reaction to fire tests for building products - Conditioning procedures and general rules for selection of substrates
EN 13501-1:2018	Fire classification of construction products and building elements Part 1: Classification using data from reaction to fire tests
EN 15102:2007+A1:2011	Decorative wall coverings - Roll and panel form products

3.2 REPORTS

Name of Laboratories	Name of sponsor	Report ref. no.	Test method
Efectis Nederland BV THE NETHERLANDS	Vescom B.V. THE NETHERLANDS	2023-Efectis-R000715 2023-Efectis-R000622	EN ISO 11925-2:2020 EN 13823:2020

3.3 TEST RESULTS

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – maximum	Compliance with parameters
EN ISO 11925-2				
Surface flame impingement	Fs ≤150 mm	6	45	-
	Ignition of filter paper		-	Compliant
Edge flame Impingement	Fs ≤150 mm	6	50	-
	Ignition of filter paper		-	Compliant

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – mean (m)	Compliance with parameters
EN 13823				
	FIGRA _{0.2MJ} [W/s]	3	56	-
	FIGRA _{0.4MJ} [W/s]		0	-
	THR _{600s} [MJ]		1.1	-
	LFS < edge		-	Compliant
	SMOGRA [m ² /s ²]		2.5	-
	TSP _{600s} [m ²]		46	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		- -	Compliant Compliant

3.4 CLASSIFICATION CRITERIA

Fire classification of construction products and building elements Excluding floorings and linear pipe thermal insulation products			
Classification criteria			
Class	B	C	D
Test method(s)			
EN ISO 11925-2 Exposure = 30 s	$F_s \leq 150$ mm within 60 s Ignition of the paper in EN ISO 11925-2 results in a d2 classification.		
EN 13823	$FIGRA_{0.2 MJ} \leq 120$ W/s LFS < edge of specimen $THR_{600s} \leq 7.5$ MJ	$FIGRA_{0.4 MJ} \leq 250$ W/s LFS < edge of specimen $THR_{600s} \leq 15$ MJ	$FIGRA_{0.4 MJ} \leq 750$ W/s
Additional classification			
Smoke production	s1 = SMOGRA ≤ 30 m ² /s ² and TSP _{600s} ≤ 50 m ² ; s2 = SMOGRA ≤ 180 m ² /s ² and TSP _{600s} ≤ 200 m ² ; s3 = not s1 or s2		
Flaming Droplets/particles	d0 = no flaming droplets/ particles in EN 13823 within 600 s; d1 = no flaming droplets/ particles persisting longer than 10 s in EN 13823 within 600 s; d2 = not d0 or d1.		

4. CLASSIFICATION AND FIELD OF APPLICATION

4.1 REFERENCE OF CLASSIFICATION

This classification has been carried out in accordance with clause 11 of EN 13501-1:2018.

4.2 CLASSIFICATION

The product, **Vinyl Wallcovering 350 g/m²**, in relation to its reaction to fire behaviour is classified:

B

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming droplets / particles is:

d0

Reaction to fire classification: B – s1, d0

4.3 FIELD OF APPLICATION

This classification is valid for the following product parameters:

Thickness	0.45 mm
Surface density	approx. 0.350 kg/m ² , glue wet/dry: 0.3 / 0.08 kg/m ²
Colour	White
Texture	Not embossed

This classification is valid for the following end use applications:

Substrate	Promatect®-H, Non-combustible calcium silicate board, 12 mm thickness (reaction to fire class A1/A2, 870 ± 50 kg/m ³ , according to EN 13238:2010)
Application	Wallcovering
Air gap	Not applicable
Methods and means of fixing	Glued to the substrate according to the manufacturer's instructions using 300 g/m ² (wet) of the wallcovering paste Vescom 3000
Joints	Vertical

4.4 DURATION OF THE VALIDITY OF THIS CLASSIFICATION REPORT

Consult classification standard and national laws and regulations for limitations on the period of validity of the classification.

5. LIMITATIONS

This classification document does not represent type approval or certification of the product.

The classification assigned to the product in this report is within the context of system 1 **Assessment and Verification of Consistency of Performance (AVCP)** and **CE marking** under the **Construction Products Regulation**.



D. van Dijk B.Eng.
Project leader Reaction to Fire



A.H.L.M. Zwinkels B.Sc.
Project leader Reaction to Fire



A. González Santamaría M.Sc.
Project leader Reaction to Fire