

**MATERIAL REACTION TO FIRE CLASSIFICATION REPORT
PREPARED IN COMPLIANCE WITH AMENDED 5 OF THE FRENCH HOME OFFICE REGULATION
REGULATION DATED NOVEMBER 21ST, 2002 (OFFICIAL GAZETTE DATED DECEMBER 31, 2002)**

Valid five years from issue date

CERTIFICATE N° 24-01136 L

And 1 Appendix of 6 pages

MATERIAL presented by: Vescom B.V.
Sint Jozefstraat 20
5753 AV Deurne
Netherland

TRADE NAME: Acton

BRIEF DESCRIPTION: Fabric 100% inherent fire resistant polyester

Nominal surface weight : 429 g/m2
Nominal thickness : 1.2 mm
Colours : Orange

TEST REPORT : N° 24-01136 E1V2 on the May 30th 2024

TESTS : Electrical burner test
Flame persistence test
Dripping test

CLASSIFICATION

M1

**Classification valid for any application for which the product is not subjected
to the CE marking of the Construction products**

CLASSIFICATION DURATION (article 5 of appendix 2) : unlimited unless otherwise specified

given the criteria resulting from the tests described in the enclosed test report.

The classification indicated does not mean that materials marketed comply with the test samples and must not be considered as a qualification certificate as defined by French law dated March 14, 2016.

N.B.: Only integral copies of this document may be made by photocopying the classification report and/or the classification report and enclosed test report.

Issued in Lyon, France, on the May 30th 2024



Olivier PALLAS
Tests and Trials Engineer



Institut Français du
Textile et de l'Habillement

Ecully, 30/05/2024

VESCOM BV

Mme BERGMANN Marion
ST. JOZEFSTRAAT 20
5753 AV DEURNE NEDERLAND
PAYS-BAS

IFTH reference : DL240422-011

TEST REPORT N° 24-01136 E1 - V2

This report cancels and replaces the one previously edited on the 24/05/2024

Only the tests marked with the symbole (*) are made under the COFRAC accreditation
The copie of this document is only authorised in its integral version

PURPOSE OF THE REQUEST

Customer reference :

Date of request : 22/04/2024

Purchase order : CO2024001505

Samples supplied on : 14/05/2024

Subject : DEV016536

N° CE/CL :

N° CQ :

SAMPLE(S) REFERENCE(S)

24-01136-001 : Acton

RESULTS SUMMARY

24-01136-001

Acton

**Buildings material - Reaction to fire - Electrical burner test
(*) NF P 92-503 (1995)**

Number of tested specimens : 4

Date of the test : 23/05/2024

Measurements	Results
Average of carbonized lengths (in mm)	162
Average of carbonized widths between 45 and 60 cm (in mm)	/
Drilling by fusion without ignition or with ignition < or = 5 s	Yes
Maximum duration of ignition (in s)	0
Fall of ardent drops or fragment fired	No
Afterglow with spread on more than 25 cm (in mm)	No

**Buildings material - Reaction to fire - Dripping test.
(*) NF P 92-505 (1995)**

Conditioning of specimens before tests : (23 ± 2)° C et (50 ± 5) % HR during minimum 7 days

Number of tested specimens : 4

Samples size : 70 X 70 mm

Date of the test : 23/05/2024

Measurements	Results
At least one sample ignited cotton	No

**Buildings material - Reaction to fire - Flame persistence test and speed of the spread of flame.
(*) NF P 92-504 (1995)**

Conditioning of specimens before tests : (23 ± 2)° C and (50 ± 5) % RH during minimum 7 days

Number of tested specimens : 4

Samples size : 460 x 230 mm

Date of the test : 23/05/2024

Measurements	Results
Maximum duration of ignition (in s)	0
Fall of ardent drops or fragment fired	No

SAMPLE DESCRIPTION ANNOUNCED BY THE CLIENT

24-01136-001	Acton
Composition	Tissu 100% polyester FR ignifugé dans la masse / Fabric 100% inherent fire resistant polyester
Mass per unit area	429 g/m ²
Thickness	1.2 mm
Color	Orange
Test requested by	Vescom B.V.
Name and address of the producer	Vescom Textiles GmbH August-Horch-Str. 16 95213 Munchberg Germany
Name and address of the supplier	Vescom B.V. Sint Jozefstraat 20 5753 AV Deurne NL

Solange SAME
Quality department



Versions

Version 1 : Report creation

Version 2 : Sample's description corrected

I.F.T.H. service clientèle

Avenue Guy de Collongue - 69134 ECULLY CEDEX
FRANCE

SIRET 433 430 832 00017



Portée disponible sur :
www.cofrac.fr
Accréditations N°:
Ecully 1-0101
Saint-Priest-en-Jarez 1-5688

Number of pages : 3 Appendices : 0

Only the tests marked with the symbole (*) are made under the COFRAC accreditation

If test reports, interpretation reports, comments, advice or observations are translated into a foreign language, only the version in French is valid.

The uncertainty associated to the result was not explicitly taken in consideration to declare the conformity to the specification.

Conformities are given only for the results associated to a specification.

Results of this test report are only valid for specimens subjected to testing at IFTH. as we received them

Report was simplified, all the technical data of the test can be communicated on request

* End of report *