

Lightfastness Textile Wallcovering VI

Testing as per ISO. 105 B method 2

Testresults are based upon 216 hours of exposure. Test was stopped at 216 hours.

Location test Tapetex BV, Helmond, Holland

Testing machinery Heraeus original Hanau Xenotest 150S

Standard blue scale 0 - 8

Humidity 65%, Blackpanel temperature 45° Celsius

Testing completed February 2015

design		result	design		result
Chandra	251250 - 251251	7	Chateau Chinon	251340 - 251344	7
silk	251252 - 251258	6	silky		
	251259	4			
	251260 - 251262	7	Chennai	251350 - 251354	7
	251263	6	silky		
	251264	7			
	251265	5	New Voyages	251360 - 251364	7
	251266 - 251267	6	silky		
	251268	3			
	251269	6	Madurai	251370 - 251379	7
	251270 - 251271	7	silky		
	251272 - 251273	6			
	251274 - 251276	5	Deep Spaces	251380 - 251384	7
	251277	6	silky		
	251278	4			
	251279	6	Kerala	251390 - 251394	5
			silky		
Shambala	251280	6			
silk	251281 - 251282	7	Princess Lace	251400 - 251404	6
	251283	6	silky		
	251284	5			
Ayesha	251290	3			
silk	251291	7			
	251292	6			
	251293	4			
	251294	6			
Lost Horizon	251300 - 251301	7			
silk	251302	5			
	251303	6			
	251304	5			
Saray	251310 - 251317	6			
silk	251318 - 251319	5			
Tabaz	251320 - 251324	6			
silk					
Sagar	251330 - 251331	7			
silk	251332 - 251333	6			
	251334	5			