

## CERTIFICATE OF TESTING

For the Account Of: Vescom  
2289 Ross Mill Road  
Henderson, NC 37536

Contact: Christine Wekilsky

Client's Identification: Syros 8047

**TEST PERFORMED** Resistance to Slippage of Yarns in Woven Fabrics Using a Standard Seam ASTM D434-95 as Modified by ASTM D3597-02(2013)

**TEST RESULTS**

Specimen	Warp Yarn Slippage (lbf)		Fill Yarn Slippage (lbf)	
	1	45.9	SB	71.9
2	40.9	SB	70.6	SB
3	39.1	SB	71.8	SB
4	53.3	SB	60.8	SB
5	42.7	SB	77.0	SB
<b>Average</b>	<b>44.4</b>		<b>70.4</b>	

**ABBREVIATIONS USED**

**SB** Seam broke before 1/4" slippage - Results should reflect this  
**SS** 1/4" slippage occurred - Note: Actual slippage of yarns is visible  
**FB** Fabric broke before 1/4" slippage - Note: Actual breakage is visible


**NOTES**

**Equipment Used:** Tinius Olson H5KT Universal Testing Machine  
**Seam Description:** Per ASTM D3597-02  
**Seam Type** Standard Lockstitch  
**Stitches per Inch** 7 -8 stitches per inch  
**Needle Used** Chrome plated 0.063 inch diameter  
**Thread** No. 24-4 hard finish Z-twist cotton thread

**ACCEPTANCE CRITERIA**

<b>A.C.T. Standard</b>	<b>Acceptance Criteria</b>
Drapery fabrics over 6oz/sq. yard	25 lbs. Minimum

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

  
 \_\_\_\_\_  
 Authorized Signature