

CERTIFICATE OF TESTING

For the Account Of: Vescom
2289 Ross Mill Road
Henderson, NC 37536

Contact: Christine Wekilsky

Client's Identification: Syros 8047

TEST PERFORMED Breaking Strength and Elongation of Textile Fabrics (Grab Test) ASTM D5034-09(2013)(G-E)

TEST RESULTS

Specimen	Breaking Force (lbf)	
1	204	
2	197	
3	205	
4	198	
5	204	
		Avg of Warp: 202
6	195	
7	196	
8	188	
9	184	
10	202	
11	187	
12	186	
13	197	
		Avg of Fill: 192


NOTES

Equipment Used: Tinius Olson H5KT Universal Testing Machine
Load Cell Maximum: 1000 pounds
Jaw Size: 1 inch x 1 inch (face and back), rubber coated
Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity
Sampling Method: As Received

ACCEPTANCE CRITERIA

A.C.T. Standard	Acceptance Criteria
Upholstery	50 pounds minimum
Panels and Upholstered Walls	35 pounds minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.



 Authorized Signature