

Vescom bv
St. Jozefstraat 20
NL-5750 AB DEURNE
NEDERLAND



Your notice of
02-03-2017

Your reference

Date
20-03-2017

Analysis Report 17.01319.07

Required tests :

EN 1021-1 (2014)

Furniture - Assessment of the ignitability of upholstered furniture - Ignition source : smouldering cigarette

EN 1021-2 (2014)

Furniture - Assessment of the ignitability of upholstered furniture – Ignition source : match flame equivalent

| Identification number | Information given by the client | Date of receipt |
|-----------------------|---------------------------------|-----------------|
| T1704898 | 701901 vinyl upholstery | 02-03-2017 |

Gina Créelle

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be

Inrichting erkend bij toepassing van de besluitwet van 30-01-1947 • Établissement reconnu par application de l'arrêté-loi du 30-01-1947
GENT • Technologiepark 7 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be
GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be
KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 281828 • fax +32 56 281830 • info@vkc.be
VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB

Reference: T1704898 - 701901 vinyl upholstery

Furniture - Assessment of the ignitability of upholstered furniture - Ignition source : smouldering cigarette

Date of ending the test 13-03-2017
Standard used EN 1021-1 (2014)

Deviation from the standard -

Conditioning 23°C, relative humidity 50%

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Water soaking of the cover No
Filling T 23140 (Recticel) - non-fire retardant foam - ± 22 kg/m³

| | 1# | 2# | 3# |
|--|--------------|--------------|--------------|
| Smouldering criteria | | | |
| Unsafe escalating combustion | no | no | no |
| Test assembly consumed | no | no | no |
| Smoulders to extremities | no | no | no |
| Smoulders through thickness | no | no | no |
| Smoulders more than 1 hour | no | no | no |
| Final examination / active smouldering | no | no | no |
| Flaming criteria | | | |
| Occurence of flames | no | no | no |
| | | | |
| | non-ignition | non-ignition | non-ignition |

cigarette fails to smoulder its complete length

Conclusion Non-ignition

Performed under accreditation in the fire lab under the responsibility of Nathan De Kock

Reference: T1704898 - 701901 vinyl upholstery

Furniture - Assessment of the ignitability of upholstered furniture – Ignition source : match flame equivalent

Date of ending the test 13-03-2017
Standard used EN 1021-2 (2014)

Deviation from the standard -

Conditioning 23°C, relative humidity 50%

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Water soaking of the cover No
Filling T 23140 (Recticel) - non-fire retardant foam - ± 22 kg/m³

Flame application time (s) 15

| | 1 | 2 | 3 |
|---|--------------|--------------|--------------|
| Smouldering criteria | | | |
| Unsafe escalating combustion | no | no | no |
| Test assembly consumed | no | no | no |
| Smoulders to extremities | no | no | no |
| Smoulders through thickness | no | no | no |
| Smoke/heat/glowing more than 60 min min | no | no | no |
| Final examination / active smouldering | no | no | no |
| Flaming criteria | | | |
| Unsafe escalating combustion | no | no | no |
| Test assembly consumed | no | no | no |
| Flames to extremities | no | no | no |
| Flames through thickness | no | no | no |
| Flaming > 120 s | no | no | no |
| Afterflame time (s) | 1 | 1 | 1 |
| | non-ignition | non-ignition | non-ignition |

Conclusion Non-ignition

Performed under accreditation in the fire lab under the responsibility of Nathan De Kock