

**Vescom bv  
Dhr. Ron Verlouw  
Postbus 70  
5753 AV DEURNE  
Nederland**



<b>Your notice of</b>	<b>Your reference</b>	<b>Date</b>
30-04-2015		20-05-2015

## **Analysis Report 15.02153.01**

Required tests :

**ISO 105-X12 (2001)**

**Determination of the colour fastness to rubbing**

Identification number	Information given by the client	Date of receipt
T1508120	SILICA	30-04-2015

Bea De Paepe

Order responsible

This report runs to 2 pages and may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.

The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

**VAT BE 0459.218.289**

CENTEXBEL-GENT  
Technologiepark 7  
BE-9052 Zwijnaarde

Tel. + 32 9 220 41 51 • Fax + 32 9 220 49 55  
gent@centexbel.be

**Fin. Acc. 210-0472965-45**

**IBAN BE44 2100 4729 6545**

CENTEXBEL-VERVIERS  
Avenue du Parc 38  
BE-4650 Herve (Chaineux)

Tel. + 32 87 32 24 30 Fax + 32 87 34 05 18  
chaineux@centexbel.be

**Reference: T1508120 - SILICA**

**Determination of the colour fastness to rubbing**

Date of ending the test 20-05-2015  
Standard used ISO 105-X12 (2001)

Deviation from the standard -  
Conditioning 20°C, relative humidity 65%  
Apparatus Crockmeter  
Applied finger Ø 16 mm  
Pressure on test specimen 9 N  
Number of cycles 10

Assessment of staining according to the grey scales (ISO 105 A03)

Numerical rating

	Wales direction	Course direction
Dry	4	4
Wet	4-5	4-5