



Report Number: 17-000631 Date: 5-3-2017

CERTIFICATE OF TESTING

For the Account Of: Raxon Fabrics

2289 Ross Mill Road

Henderson, NC 27536

Contact: Barbara Crane

Client's Identification: Clare 8052 Test #464

TEST PERFORMED NFPA 701 Standard Methods of Fire Test for Flame Propagation of Textiles and Films 2015 – Test #1

TEST RESULTS

Specimen	Initial Mass (g)	Final Mass (g)	Mass Loss (%)	Flaming Drip (s)	Afterflame (s)
1	3.9	2.9	26%	0	0
2	3.9	2.7	29%	0	0
3	3.9	3.4	12%	0	0
4	3.9	3.0	24%	0	0
5	3.9	3.2	18%	0	0
6	3.9	3.0	24%	0	0
7	3.9	2.9	27%	0	0
8	3.9	2.8	30%	0	0
9	3.9	2.9	25%	0	0
10	3.9	2.8	27%	0	0
Average	3.9	2.9	24%	0.0	0.0

Approximate weight (oz./sq. yd): 1.9

Product Configuration:		
------------------------	--	--

Conditioning: ☐ 70 ±2°F & 65 ±2%RH for minimum 24 hours

Intended End-use (if known & other than drapery):

ACCEPTANCE CRITERIA

Afterflame is required to be recorded; however, it is not factored into the Acceptance Criteria

- 1. Where fragments or residues of specimens that fall to the floor of the test chamber continue to burn for more than an average of 2 seconds per specimen for the sample of 10 specimens, the material shall be recorded as failing. (Flaming Drip)
- 2. Where the average weight loss of the 10 specimens in a sample is greater than 40 percent, the material shall be recorded as failing.
- 3. Individual specimens will be listed as a failure if it exceeds mean + 3 SD
- 4. Where the specimens do not demonstrate performance in accordance with either of the conditions indicated above, the material shall be recorded as passing this test and shall be designated as flame resistant.

	Based on the above Results and Acceptance Criteria, the item tested: Complies Does Not Comply
	Testing of 10 additional specimens is required

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

aneus	
Authorized Signature CR	