



Report Number: 17-002078

Revision Number:1

Date Order Received: 07/10/2017

For the Account of:

Vescom BV Sint Jozefstraat 20 NL-5753 AV Deurne

Client's Identification:	Faray 8007-8054	

CERTIFICATE OF TESTING

TEST PERFORMED: NFPA 701 Standard Methods of Fire Test for Flame Propagation of Textiles and Films 2015 - Test #1

TEST RESULTS

Specimen	Mass Initial (g)	Mass Final (g)	Mass Loss (%)	Drip Burn (s)	Afterflame (s)
1	13.0	8.3	36	0.0	0.0
2	13.2	8.5	36	0.0	0.0
3	13.2	10.0	24	0.0	0.0
4	13.1	8.4	36	0.0	0.0
5	13.1	9.7	26	0.0	0.0
6	13.3	11.3	15	0.0	0.0
7	13.3	9.8	26	0.0	0.0
8	13.2	9.5	28	0.0	0.0
9	13.4	9.0	33	0.0	0.0
10	13.1	9.8	25	0.0	0.0
Average	13.2	9.4	29	0.0	0.0

Approximate weigh	it (oz./sq. yd): 6.5	Standard Deviation: 6.8	Average + 3 SD: 49.4
Product Configurat	ion: 🗵 Single Lay	er	
Conditioning:	⊠ Oven at 22	20°F for minimum 30 minutes	☐ 70 ±2°F & 65 ±2%RH for minimum 24 hours
Intended End-use (if known & other than draper	y): Drapery	
ACCEPTANCE CRI	ΓERIA		
Afterflame is require	ed to be recorded; however, it	is not factored into the Acceptance Ci	riteria
	•	ens that fall to the floor of the test cha of 10 specimens, the material shall be	amber continue to burn for more than an average of 2 recorded as failing. (Flaming Drip)
Where the	e average weight loss of the 1	0 specimens in a sample is greater th	an 40 percent, the material shall be recorded as failing.
	•	failure if it exceeds mean + 3 SD	
	'	ate performance in accordance with e all be designated as flame resistant.	ither of the conditions indicated above, the material shall
CONCLUSION	Based on the above Results	and Acceptance Criteria, the item test	ed:
	☐ Does Not Comply		
	•	ere obtained after testing specimen in	accordance with the procedures and equipment
specified by the star	ndard stated above.		
Musik	<u> </u>		
_ 0			

553 76th Street, Byron Center, MI 49315

Authorized Signature

P: 616-559-6123 E: testlab@applied-textiles.com

Page 1 of 1

Date Order Completed: 07/26/2017