



TESTING CERT. #3193.01

Report Number: 17-001057 Revision Number:1 Date Order Received: 05/23/2017

For the Account of:

Raxon Fabrics 2289 Ross Mill Road Henderson, NC 37536

Client's Identification:

Fuga 7047 Vescom Test #475

CERTIFICATE OF TESTING

TEST PERFORMED: Resistance to Slippage of Yarns in Woven Fabrics Using a Standard Seam ASTM D4034-92

TEST RESULTS					
Specime	en Warp Yarn Slippage (lbf)	Type of Failure	Specimen	Fill Yarn Slippage (lbf)	Type of Failure
1	37.4	SS	1	99.0	SB
2	39.2	SS	2	105.0	SB
3	37.3	SS	3	112.0	SB
4	45.6	SS	4	82.2	SB
5	42.4	SS	5	99.7	SB
Avg. Wa	rp 40.5		Avg. Fill	99.5	

ABBREVIATIONS USED

SB Seam broke before 1/4" slippage - Results should reflect this

SS 1/4" slippage occurred - Note: Actual slippage of yarns is visible

FB Fabric broke before 1/4" slippage - Note: Actual breakage is visible

NOTES

Equipment Used:

Tinius Olson H5KT Universal Testing Machine

Seam Description:

Seam Type	Standard Lockstitch	
Stitches per Inch	7 ± 0.5 stitches per inch	
Needle Used	Size 22 NM: 140, 135x17 ball point needle	
Thread	Nymo EX Bonded Nylon thread; 5x is used for the bobbin and 8x is used for the needle	

ACCEPTANCE CRITERIA

A.C.T. Standard	Acceptance Criteria
Upholstery	25 lbs. Minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

Date Order Completed: 05/30/2017

553 76th Street, Byron Center, MI 49315

P: 616-559-6123 E: testlab@applied-textiles.com

Page 1 of 1

This laboratory test is not intended to reflect fabric performance under actual conditions. The certification procedure merely measures the performance of samples under the predetermined and specific test conditions prescribed by the standard specified. This certificate applies only to the standards or processing identified and to the random sample(s) tested. The test results are representative of the qualities of the piece or lot only to the standards or processing identified and to the random sample(s) tested. The test results are representative of the qualities of the piece or lot only to the standards or processing identified and to the random sample(s) tested. The test results are representative of the qualities of the piece or lot only to the standard specific test.

Our reports and letters are for the exclusive use of the customer to whom they are addressed and they and the corporation named on the reverse are not to be used under any circumstances without prior written approval. Samples will not be retained, unless specified by the customer. Retained samples will be kept a maximum time of one year unless a specific retention period is necessary.