



TESTING CERT. #3193.01

Report Number: 17-001057 Revision Number:1 Date Order Received: 05/23/2017

For the Account of:

Raxon Fabrics 2289 Ross Mill Road Henderson, NC 37536

Client's Identification:

Fuga 7047 Vescom Test #475

CERTIFICATE OF TESTING

TEST PERFORMED: Abrasion Resistance of Textile Fabrics (Oscillatory Cylinder Method) ASTM D4157-13

TEST RESULTS				
	Number of Double Rubs	Warp (Length) Specimens	Fill (Width) Specimens	
Specimen #1	40,000	Breakage occurred	Slight wear	
Specimen #2	85,000	Breakage occurred	No breakage or appreciable wear	
INTERPRETATION USED				
区 Option 1		The end point is reached on a woven fabric when two or more yarns have broken or on a knitted fabric, when a hole appears.		
Option 2		The end point is reached when there is a change in shade or appearance that is sufficient to cause a		
NOTES				
Abradant Used: XACT Standard #10 Cotton Duck Vire Screen				
Samples Backed with				
Masking Tape:	□ Yes ⊠ No			
Tension:	4 pounds			
Compression:	3 pounds			
ACCEPTANCE CRITERIA				
A.C.T. Standard	Acceptance Crite	eria		
1 2 1		reakage or wear after 15,000 double rubs		
Heavy Duty Upholstery No appreciable breakage or wear after 30,000 double rubs				
CONCLUSION Based on the above Results and the A.C.T. Standard, the item tested:				
	General Contract Upholstery			
I Heavy Duty Upholstery				

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

AME

Authorized Signature

Date Order Completed: 05/31/2017

553 76th Street, Byron Center, MI 49315

P: 616-559-6123 E: testlab@applied-textiles.com

Page 1 of 1

This laboratory test is not intended to reflect fabric performance under actual conditions. The certification procedure merely measures the performance of samples under the predetermined and specific test conditions prescribed by the standard specified. This certificate applies only to the standards or processing identified and to the random sample(s) tested. The test results are representative of the qualities of the piece or lot only to the standards is representative of the piece or lot.

Our reports and letters are for the exclusive use of the customer to whom they are addressed and they and the corporation named on the reverse are not to be used under any circumstances without prior written approval. Samples will not be retained, unless specified by the customer. Retained samples will be kept a maximum time of one year unless a specific retention period is necessary.