



Report Number: 18-001601

Revision Number:1

Date Order Received: 03/15/2018

For the Account of:

Vescom America Inc. 2289 Ross Mill Road Henderson, NC 272537

Client's Identification:	Nora 8032 Test #608
CHELL'S IUCHUICAUUH.	11010 0032 1531 #000

CERTIFICATE OF TESTING

TEST PERFORMED: NFPA 701 Standard Methods of Fire Test for Flame Propagation of Textiles and Films 2015 – Test #1

TEST RESULTS

Specimen	Mass Initial (g)	Mass Final (g)	Mass Loss (%)	Drip Burn (s)	Afterflame (s)
1	6.0	3.7	38	0.0	0.0
2	5.8	3.3	43	0.0	0.0
3	5.9	4.1	31	0.0	0.0
4	5.7	4.4	23	0.0	0.0
5	5.8	3.8	34	0.0	0.0
6	5.7	3.4	40	0.0	0.0
7	5.7	3.3	42	0.0	0.0
8	5.8	3.4	41	0.0	0.0
9	5.9	4.1	31	0.0	0.0
10	5.8	3.8	34	0.0	0.0
Average	5.8	3.7	36	0.0	0.0

Approximate weigh	t (oz./sq. yd): 2.9	Standard Deviation: 6.3	Average + 3 SD: 54.9
Product Configurat	ion: 🗵 Single Laye	r 🔲 Multi Layer	
Conditioning: ☑ Oven at 220°F for minimum		0°F for minimum 30 minutes	☐ 70 ±2°F & 65 ±2%RH for minimum 24 hours
Intended End-use (f known & other than drapery): Drapery	
ACCEPTANCE CRI	ΓERIA		
Afterflame is require	ed to be recorded; however, it is	s not factored into the Acceptance Ci	riteria
	•		amber continue to burn for more than an average of 2
		10 specimens, the material shall be	3 \ 3 \ 1 /
			an 40 percent, the material shall be recorded as failing.
	•	ailure if it exceeds mean + 3 SD te performance in accordance with e	ither of the conditions indicated above, the material shall
	•	Ill be designated as flame resistant.	inter of the conditions indicated above, the material shall
CONCLUSION	Based on the above Results a	nd Acceptance Criteria, the item test	ed:
	☐ Does Not Comply		
CERTIFICATION c	ertify that the above results we	re obtained after testing specimen in	accordance with the procedures and equipment
specified by the star	ndard stated above.		
Chelsea hybis	ii		
or account to			
Authorized Signature			Date Order Completed: 03/19/2018

553 76th Street, Byron Center, MI 49315

P: 616-559-6123 E: testlab@applied-textiles.com

Page 1 of 1