



Report Number: 18-001297 Revision Number:1 Date Order Received: 03/01/2018

For the Account of:

Vescom America Inc. 2289 Ross Mill Road Henderson, NC 272537

Client's Identification:

Burton 7056 Test #603

## **CERTIFICATE** OF TESTING

TEST PERFORMED: Resistance to Slippage of Yarns in Woven Fabrics Using a Standard Seam ASTM D4034-92

TEST RESULTS						
Specimen	Warp Yarn Slippage (lbf)	Type of Failure	Specimen	Fill Yarn Slippage (lbf)	Type of Failure	
1	86.0	SB	1	104.0	SB	
2	104.0	SB	2	116.0	SB	
3	109.0	SB	3	107.0	SB	
4	98.9	SB	4	105.0	SB	
5	107.0	SB	5	102.0	SB	
Avg. Warp	101.0		Avg. Fill	107.0		

## ABBREVIATIONS USED

SB Seam broke before 1/4" slippage - Results should reflect this

**SS** 1/4" slippage occurred - Note: Actual slippage of yarns is visible

FB Fabric broke before 1/4" slippage - Note: Actual breakage is visible

## NOTES

Equipment Used:

Tinius Olson H5KT Universal Testing Machine

Seam Description:

Seam Type	Standard Lockstitch	
Stitches per Inch	7 ± 0.5 stitches per inch	
Needle Used	Size 22 NM: 140, 135x17 ball point needle	
Thread	Nymo EX Bonded Nylon thread; 5x is used for the bobbin and 8x is used for the needle	

## ACCEPTANCE CRITERIA

A.C.T. StandardAcceptance CriteriaUpholstery25 lbs. Minimum

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver

Authorized Signature

Date Order Completed: 03/07/2018

553 76th Street, Byron Center, MI 49315

P: 616-559-6123 E: testlab@applied-textiles.com

Page 1 of 1

This laboratory test is not intended to reflect fabric performance under actual conditions. The certification procedure merely measures the performance of samples under the predetermined and specific test conditions prescribed by the standard specified. This certificate applies only to the standards or processing identified and to the random sample(s) tested. The test results are representative of the qualities of the piece or lot only to the standards or processing identified and to the random sample(s) tested. The test results are representative of the qualities of the piece or lot only to the standards or processing identified and to the random sample(s) tested. The test results are representative of the qualities of the piece or lot only to the standard specific test.

Our reports and letters are for the exclusive use of the customer to whom they are addressed and they and the corporation named on the reverse are not to be used under any circumstances without prior written approval. Samples will not be retained, unless specified by the customer. Retained samples will be kept a maximum time of one year unless a specific retention period is necessary.