



Report Number: 18-001201

Revision Number:1

Date Order Received: 02/27/2018

For the Account of: Vescom America Inc.

2289 Ross Mill Road Henderson, NC 272537

Client's Identification: Lindau 7028 Test #604

CERTIFICATE OF TESTING

TEST PERFORMED: Breaking Strength and Elongation of Textile Fabrics (Grab Test) ASTM D5034-09(2017)(G-E)

TEST RESULTS

	Specimen	Breaking Ford
		lbf
Warp	1	185
	2	182
	3	188
	4	182
	5	191
	Average	186
Fill	1	225
	2	226
	3	223
	4	215
	5	237
	6	218
	7	225
	8	224
	Average	224

NOTES

Equipment Used: Tinius Olson H5KT Universal Testing Machine

Load Cell Maximum: 1000 pounds

Jaw Size: 1 inch x 1 inch (face and back), rubber coated

Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity

Sampling Method: As Received

ACCEPTANCE CRITERIA

A.C.T. Standard
Upholstery
Panels and Upholstered Walls
Acceptance Criteria
50 pounds minimum
35 pounds minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Jolla Saver

Authorized Signature Date Order Completed: 03/02/2018