



Report Number: 18-001189 Revision Number:1 Date Order Received: 02/27/2018

For the Account of:

Vescom America Inc. 2289 Ross Mill Road Henderson, NC 272537

Client's Identification:

Ariana Test #602

CERTIFICATE OF TESTING

TEST PERFORMED: Breaking Strength and Elongation of Textile Fabrics (Grab Test) ASTM D5034-09(2017)(G-E)

TEST RESULTS

	Specimen	Breaking Force
		lbf
Warp	1	86
	2	69
	3	78
	4	69
	5	72
	Average	75
Fill	1	150
	2	143
	3	145
	4	151
	5	147
	6	147
	7	129
	8	149
	Average	145

NOTES

Equipment Used:	Tinius Olson H5KT Universal Testing Machine
Load Cell Maximum:	1000 pounds
Jaw Size:	1 inch x 1 inch (face and back), rubber coated
Test Conditions:	70 ±4°F, 65 ±5% Relative Humidity
Sampling Method:	As Received

ACCEPTANCE CRITERIA

A.C.T. StandardAcceptance CriteriaUpholstery50 pounds minimumPanels and Upholstered Walls35 pounds minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Chelsea kyluski

Authorized Signature

Date Order Completed: 03/02/2018

553 76th Street, Byron Center, MI 49315

P: 616-559-6123 E: testlab@applied-textiles.com

Page 1 of 1

This laboratory test is not intended to reflect fabric performance under actual conditions. The certification procedure merely measures the performance of samples under the predetermined and specific test conditions prescribed by the standard specified. This certificate applies only to the standards or processing identified and to the random sample(s) tested. The test results are representative of the qualities of the piece or lot only to the standards or processing identified and to the random sample(s) tested. The test results are representative of the qualities of the piece or lot only to the standards or processing identified and to the random sample(s) tested. The test results are representative of the qualities of the piece or lot only to the standard specified to the sample tested is representative of the piece or lot.

Our reports and letters are for the exclusive use of the customer to whom they are addressed and they and the corporation named on the reverse are not to be used under any circumstances without prior written approval. Samples will not be retained, unless specified by the customer. Retained samples will be kept a maximum time of one year unless a specific retention period is necessary.