



Report Number: 18-001607

Revision Number:1

Date Order Received: 03/15/2018

For the Account of: Vescom America Inc.

2289 Ross Mill Road Henderson, NC 272537

Client's Identification: Noss 7058 Test #606

CERTIFICATE OF TESTING

TEST PERFORMED: Breaking Strength and Elongation of Textile Fabrics (Grab Test) ASTM D5034-09(2017)(G-E)

TEST RESULTS

	Specimen	Breaking Force
		lbf
Warp	1	507
	2	529
	3	535
	4	540
	5	508
	Average	524
Fill	1	354
	2	340
	3	339
	4	348
	5	313
	6	334
	7	327
	8	338
	Average	337

NOTES

Equipment Used: Tinius Olson H5KT Universal Testing Machine

Load Cell Maximum: 1000 pounds

Jaw Size: 1 inch x 1 inch (face and back), rubber coated

Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity

Sampling Method: As Received

ACCEPTANCE CRITERIA

A.C.T. Standard
Upholstery
Panels and Upholstered Walls
Acceptance Criteria
50 pounds minimum
35 pounds minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

00000

Authorized Signature Date Order Completed: 03/23/2018