Vescom B.V. St. Jozefstraat 20 5753 AV Deurne **Nederland**



Your notice of 07-09-2015

Your reference

Date 26-04-2016

Analysis Report 15.04219.03

Required tests:

EN 13773 (2003)

Identification number	Information given by the client	Date of receipt
T1516202	Moroni	28-09-2015

Gina Créelle

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be Inrichting erkend bij toepassing van de besluitwet van 30-01-1947 • Établissement reconnu par application de l'arrêté-loi du 30-01-1947 GENT • Technologiepark 7 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 281828 • fax +32 56 281830 • info@vkc.be VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB

Reference: T1516202 - Moroni

Washing and drying

Date of ending the test 01-10-2015

Standard used ISO 6330 (2000) + A1 (2008), ISO 6330 (2012)

Deviation from the standard -

Apparatus Wascator FOM 71 (type A)
Used detergent ECE detergent (Type 3)

Washing method and temperature 8A- 30°C (2000) Drying method A = Line dry (2000)

Number of washing cycles 12 Mass of the test specimens 1526 g

Sample generated: T1516202_01d

Reference: T1516202_01d - Moroni

<u>Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.</u>

Date of ending the test 07-10-2015

Standard used EN 1101 (1995) + A1 (2005)

Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

Ignition Bottom edge

The test specimens have been cleaned.

Length

Flame application	Cases of	Cases of		
time (s)	ignition	non-ignition		
1	0	1		
2	0	1		
3	0	1		
4	0	1		
5	0	1		
10	0	1		
15	0	1		
20	0	5		

The mean of the recorded times at which ignition was observed is calculated No ignition within $20\ \mathrm{s}$

Width

Flame application	Cases of	Cases of		
time (s)	ignition	non-ignition		
1	0	1		
2	0	1		
3	0	1		
4	0	1		
5	0	1		
10	0	1		
15	0	1		
20	0	5		

The mean of the recorded times at which ignition was observed is calculated No ignition within $20\ \mathrm{s}$

Reference: T1516202_01d - Moroni

<u>Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.</u>

Date of ending the test 15-10-2015 Standard used EN 13772 (2011) Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have been cleaned.

Length

	Face A	Face B	Face B	Face B
Severance 220 mm thread	no	no	no	no
Severance 370 mm thread	no	no	no	no
Severance 520 mm thread	no	no	no	no
Time to sever 520 mm thread (s)	/	/	/	/
Destroyed length (mm)	145	165	170	170
Flaming debris	no	no	no	no

Width

	Face A	Face B	Face B	Face B
Severance 220 mm thread	no	no	no	no
Severance 370 mm thread	no	no	no	no
Severance 520 mm thread	no	no	no	no
Time to sever 520 mm thread (s)	/	/	/	/
Destroyed length (mm)	130	165	165	155
Flaming debris	no	no	no	no

Classification in accordance with EN 13773 Class 1