



Report Number: 18-001188

Revision Number:1

Date Order Received: 02/27/2018

For the Account of: Vescom America Inc. 2289 Ross Mill Road

Henderson, NC 272537

Client's Identification: Zanzibar Test #600

CERTIFICATE OF TESTING

TEST PERFORMED: Breaking Strength and Elongation of Textile Fabrics (Grab Test) ASTM D5034-09(2017)(G-E)

TEST RESULTS

	Specimen	Breaking Ford
	•	lbf
Warp	1	133
	2	138
	3	142
	4	126
	5	139
	Average	136
Fill	1	99
	2	103
	3	101
	4	110
	5	107
	6	117
	7	111
	8	109
	Average	107

NOTES

Equipment Used: Tinius Olson H5KT Universal Testing Machine

Load Cell Maximum: 1000 pounds

Jaw Size: 1 inch x 1 inch (face and back), rubber coated

Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity

Sampling Method: As Received

ACCEPTANCE CRITERIA

A.C.T. Standard
Upholstery
Panels and Upholstered Walls
Acceptance Criteria
50 pounds minimum
35 pounds minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Million right since

Authorized Signature Date Order Completed: 03/02/2018