



Report Number: 19-003300

Revision Number:1

Date Order Received: 06/18/2019

For the Account of: Vescom, B.V.
Sint Jozestraat 20

5753 Av Duerne

Client's Identifica	ation: Bowen			
		FICATE OF TESTING	OTM D 4457 40(0047)	
TEST PERFORM	MED: Abrasion Resistance of Textile Fabr	rics (Oscillatory Cylinder Method) <i>F</i>	ASTM D4157-13(2017)	
TEST RESULTS				
Number of Double Rubs		Warp (Length) Specimens	Fill (Width) Specimens	
Specimen #1	30,000	Breakage occurred	Breakage occurred	
Specimen #2	35,000	Breakage occurred	No breakage or appreciable wear	
INTERPRETATION	NUSED			
	The end point is reached on a woven when a hole appears.	The end point is reached on a woven fabric when two or more yarns have broken or on a knitted fabric, when a hole appears.		
☐ Option 2	The end point is reached when there i customer to complain.	The end point is reached when there is a change in shade or appearance that is sufficient to cause a customer to complain.		
NOTES				
Abradant Used: Samples Backed	☑ ACT Standard #10 Cotton Du with	ck		
Masking Tape Tension:				
Compression:	4 pounds 3 pounds			
ACCEPTANCE CF				
A.C.T. Standard Acceptance Criteria General Contract Upholstery No appreciable breakage		ge or wear after 15,000 double rubs		
, , , , , , , , , , , , , , , , , , , ,		ge or wear after 30,000 double rubs		
CONCLUSION	Based on the above Results and the A.C.T	. Standard, the item tested:		
	☐ Unrated			
	☐ General Contract Upholstery ☑ Heavy Duty Upholstery			
	Est fleavy Buty Ophiolistery			
	certify that the above results were obtained a andard stated above.	after testing specimen in accordance w	rith the procedures and equipment	
Berta Sti	Jer.			
Authorized Signature			Date Order Completed: 06/21/2019	

553 76th Street, Byron Center, MI 49315

P: 616-559-6123 E: testlab@applied-textiles.com

Page 1 of 1