



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

January 24, 2017

Ms. Barbara Crane
VESCOB B.V.
Sint Jozestraat
5753 Av Duerne

Reference: Laboratory Test Report
Lab Identification No. 23322
Invoice No. 54504

Dear Ms. Crane:

One (1) fabric sample, identified as **DOLIN DRAPERY 8048.02 TEST # 407 FR POLY 13 OZ/YD**, was received and tested in accordance with the test procedures outlined. The results are as follows:

Test Procedures

Test Results

	<u>Warp</u>	<u>Fill</u>
Yarn Slippage (lbf) ASTM D 434-95	32.3	30.1
Colorfastness to Crocking AATCC 8-2013		Dry – 5 Wet – 5

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

January 24, 2017

Ms. Barbara Crane
VESCOB B.V.
Sint Jozestraat
5753 Av Duerne

Reference: Laboratory Test Report
Lab Identification No. 23322
Invoice No. 54504

Dear Ms. Crane:

One (1) fabric sample, identified as **DOLIN DRAPERY 8048.02 TEST # 407 FR POLY 13 OZ/YD**, was received and tested in accordance with AATCC Test Method 16.3-2014, “Colorfastness to Light: Xenon-Arc”. The sample was tested for a total of 60 Standard Hours. The results are as follows:

Test Results After

60 Std. Hrs.

3


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

January 24, 2017

Ms. Barbara Crane
VESCOB B.V.
Sint Jozestraat
5753 Av Duerne

Reference: Laboratory Test Report
Lab Identification No. 23322
Invoice No. 54504

Dear Ms. Crane:

One (1) fabric sample, identified as **DOLIN DRAPERY 8048.02 TEST # 407 FR POLY 13 OZ/YD**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2015 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Test Results</u>	
	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	11.23
2	0.0	20.80
3	0.0	17.38
4	0.0	22.06
5	0.0	19.34
6	0.0	20.50
7	0.0	20.83
8	0.0	17.27
9	0.0	21.18
<u>10</u>	<u>0.0</u>	<u>21.67</u>
AVG	0.0	19.23

The fabric sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

