



Received: 10/24/2017 | Completed: 10/31/2017 | Letter: P5 | RV | P.O.#: | Test Report #: 3-21942-5-

Client's Identification | Style: PVC Vinyl Upholstery. Content: PVC Vinyl Upholstery. Weight: 38.515 oz/lyd. Product End Use: Upholstery. Thickness: 0.0460in.

Tested For: **Damian Maldonado** | Key Test: ASTM D 4157/ACT Coated 100K 484  
 Vescom America | Tel: 1-(252)-431-6233 | Ext:  
 PO Box 1198 | Fax: 1-( )- -  
 Henderson, NC 27537

RESULTS: Visual Observations (see page 1 for Rating System)

| # of Double Rubs | Length Specimens                    | Width Specimens                     |
|------------------|-------------------------------------|-------------------------------------|
| 3,000            | 5                                   | 5                                   |
| 9,000            | 5                                   | 5                                   |
| 15,000           | 5                                   | 5                                   |
| 22,500           | 5                                   | 5                                   |
| 30,000           | 4.5                                 | 4.5                                 |
| 40,000           | 4.5                                 | 4.5                                 |
| 50,000           | 4.5                                 | 4.5                                 |
| 60,000           | 4.5                                 | 4.5                                 |
| 70,000           | 4.5                                 | 4.5                                 |
| 80,000           | 4.5                                 | 4.5                                 |
| 90,000           | 4.5                                 | 4.5                                 |
| 100,000          | 4.5                                 | 4.5                                 |
|                  | Very slight loss of surface texture | Very slight loss of surface texture |

NOTE: For tests exceeding 100,000 double rubs, the cotton duck abradant is changed after every 100,000 double rubs.

REMARKS: None.


ACCEPTANCE CRITERIA:

High Traffic/Public Spaces: No noticeable wear after 50,000 double rubs (Minimum rating of 3)

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested is rated for:

High Traffic/Public Spaces;  Unrated

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

  
 AUTHORIZED SIGNATURE  
 GOVMARK  
 MA-2 /pm/AC

Phyllis Pettit

NOV 09 2017