



Vescom bv
Sint-Jozefstraat 20
5753 AV Deurne
NEDERLAND

Your notice of
25-01-2019

Your reference

Date
05-03-2019

Analysis Report 19.00464.01

Required tests :

BS 5867-2 (2008)

Identification number	Information given by the client	Date of receipt
T1901856	Tay 8077	25-01-2019



Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

Reference: T1901856 - Tay 8077

Fabrics for curtains, drapes and window blinds – Flammability requirements

Date of ending the test 05-03-2019
Standard used EN ISO 15025 (2002)
Product standard BS 5867-2 (2008)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Flame application time (s) 5

	Afterflame time (s)	Afterglow time (s)	Flame or hole on edge	Flaming debris
Length front	0.0	0.0	no	no
Length back	0.0	0.0	no	no
Width front	0.0	0.0	no	no
Width back	0.0	0.0	no	no
Average	0.0	0.0		

Flame application time (s) 15

	Afterflame time (s)	Afterglow time (s)	Flame or hole on edge	Flaming debris
Length front	0.0	0.0	no	no
Length back	0.0	0.0	no	no
Width front	0.0	0.0	no	no
Width back	0.0	0.0	no	no
Average	0.0	0.0		



Flame application time (s) 20

	Afterflame time (s)	Afterglow time (s)	Flame or hole on edge	Flaming debris
Length front	0.0	0.0	no	no
Length back	0.0	0.0	no	no
Width front	0.0	0.0	no	no
Width back	0.0	0.0	no	no
Average	0.0	0.0		

Flame application time (s) 30

	Afterflame time (s)	Afterglow time (s)	Flame or hole on edge	Flaming debris
Length front	0.0	0.0	no	no
Length back	0.0	0.0	no	no
Width front	0.0	0.0	no	no
Width back	0.0	0.0	no	no
Average	0.0	0.0		

Type C performance requirements

The mean afterflame or afterglow times shall not exceed 2,5 s

No part of any hole nor any part of the lowest boundary of any flame shall reach the top edge or either vertical edge.

There shall be no separation of any flaming debris.

Conclusion Flammability, of the unwashed fabric, complies with the requirements of BS 5867-2:2008, type "C"