



Vescom Textiles GmbH
Ms. Marion Bergmann
August-Horch-Str. 16
95213 MÜNCHBERG
Duitsland

Your notice of
 15-07-2019

Your reference

Date
 17-09-2019

Analysis Report 19.04161.02

Required tests :

IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8	Fire tests - Test for upholstered furniture - smouldering cigarette test
IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8	Fire tests - Test for upholstered furniture - Match flame equivalent

Identification number	Information given by the client	Date of receipt
T1915898	TOGO	15-07-2019



Petra Wittevrongel
 Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T1915898 - TOGO

IMO upholstered furniture

Information given by the client

Type of furniture

Upholstery

Fabric

Composition

70% mohair - 30% silk (basis: cotton)

Thickness in mm

2

Weight g/m²

546

Colour

Beige

Fire retardant treatment

No



Reference: T1915898 - TOGO

Fire tests - Test for upholstered furniture - smouldering cigarette test


Date of ending the test 11-09-2019
Standard used IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8
Deviation from the standard -
Conditioning 23°C, relative humidity 50%

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Filling T 23140 (Recticel) * - non-fire retardant foam - $\pm 22 \text{ kg/m}^3$
* standard non-FR PU-foam (as indicated in Appendix 2 and 3 of Part 8)


Ignition source: smouldering cigarette with the following specifications

Length: $(70 \pm 4) \text{ mm}$
Diameter: $(8.0 \pm 0.5) \text{ mm}$
Mass: $(0.95 \pm 0.15) \text{ mm}$
Smouldering rate: $(11.0 \pm 4.0) \text{ min} / 50 \text{ mm}$



	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Smoulders more than 1 hour	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Occurrence of flames	no	no
	non-ignition	non-ignition

Conclusion Pass



Reference: T1915898 - TOGO

Fire tests - Test for upholstered furniture - Match flame equivalent

Date of ending the test 11-09-2019
 Standard used IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8
 Deviation from the standard -
 Conditioning 23°C, relative humidity 50%

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Filling T 23140 (Recticel) * - non-fire retardant foam - ± 22 kg/m³
 * standard non-FR PU-foam (as indicated in Appendix 2 and 3 of Part 8)

Flame application time (s) 20

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke/heat/glowing more than 120 s	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Flaming > 120 s	no	no
Afterflame time (s)	0	0
	non-ignition	non-ignition

Conclusion Pass