



**Vescom B.V.**  
**Sint Jozefstraat 20**  
**NL-5753 AV Deurne**  
**Nederland**

**Your notice of**  
12-03-2020

**Your reference**

**Date**  
28-04-2020

## Analysis Report 20.01487.01

Required tests :

**BS 5867-2 (2008)**

| Identification number | Information given by the client | Date of receipt |
|-----------------------|---------------------------------|-----------------|
| T2005622              | Liran                           | 12-03-2020      |



**Gina Créelle**  
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

**Reference: T2005622 - Liran**

**Fabrics for curtains, drapes and window blinds – Flammability requirements**

Date of ending the test 27-04-2020  
 Standard used EN ISO 15025 (2002)  
 Product standard BS 5867-2 (2008)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Flame application time (s) 5

|              | Afterflame time (s) | Afterglow time (s) | Flame or hole on edge | Flaming debris |
|--------------|---------------------|--------------------|-----------------------|----------------|
| Length front | 0.0                 | 0.0                | no                    | no             |
| Length back  | 0.0                 | 0.0                | no                    | no             |
| Width front  | 0.0                 | 0.0                | no                    | no             |
| Width back   | 0.0                 | 0.0                | no                    | no             |
| Average      | 0.0                 | 0.0                |                       |                |

Flame application time (s) 15

|              | Afterflame time (s) | Afterglow time (s) | Flame or hole on edge | Flaming debris |
|--------------|---------------------|--------------------|-----------------------|----------------|
| Length front | 0.0                 | 0.0                | no                    | no             |
| Length back  | 0.0                 | 0.0                | no                    | no             |
| Width front  | 0.0                 | 0.0                | no                    | no             |
| Width back   | 0.0                 | 0.0                | no                    | no             |
| Average      | 0.0                 | 0.0                |                       |                |



Flame application time (s) 20

|              | Afterflame time (s) | Afterglow time (s) | Flame or hole on edge | Flaming debris |
|--------------|---------------------|--------------------|-----------------------|----------------|
| Length front | 0.0                 | 0.0                | no                    | no             |
| Length back  | 0.0                 | 0.0                | no                    | no             |
| Width front  | 0.0                 | 0.0                | no                    | no             |
| Width back   | 0.0                 | 0.0                | no                    | no             |
| Average      | 0.0                 | 0.0                |                       |                |

Flame application time (s) 30

|              | Afterflame time (s) | Afterglow time (s) | Flame or hole on edge | Flaming debris |
|--------------|---------------------|--------------------|-----------------------|----------------|
| Length front | 0.0                 | 0.0                | no                    | no             |
| Length back  | 0.0                 | 0.0                | no                    | no             |
| Width front  | 0.0                 | 0.0                | no                    | no             |
| Width back   | 0.0                 | 0.0                | no                    | no             |
| Average      | 0.0                 | 0.0                |                       |                |

#### Type C performance requirements

The mean afterflame or afterglow times shall not exceed 2,5 s

No part of any hole nor any part of the lowest boundary of any flame shall reach the top edge or either vertical edge.

There shall be no separation of any flaming debris.

Conclusion Flammability, of the unwashed fabric, complies with the requirements of BS 5867-2:2008, type "C"