



**Vescom bv**  
**Dhr. Frank Teeuwen**  
**Sint-Jozefstraat 20**  
**5753 AV DEURNE**  
**Netherlands**

**Your notice of**  
 17-06-2020

**Your reference**

**Date**  
 06-07-2020

## Analysis Report 20.03806.01

Required tests :

**ISO 105-B02 (2014)**

**Determination of the colour fastness to light**

Identification number	Information given by the client	Date of receipt
T2013261	Furka Plus 7064.21	17-06-2020
T2013262	Furka Plus 7064.10	17-06-2020
T2013263	Furka Plus 7064.09	17-06-2020



Petra Wittevrongel  
 Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



**Reference: T2013261 - Furka Plus 7064.21**

**Determination of the colour fastness to light**

Date of ending the test	03-07-2020
Standard used	ISO 105-B02 (2014)
Deviation from the standard	-
Method	1
Apparatus	Xenotest 220+ Atlas
Exposure	Constant
Irradiance	42 W/m <sup>2</sup> @ 300-400 nm
Black standard temperature	47±3°C
Effective humidity	±40%

Assessment according the blue scale standard  
Numerical rating Blue scale grade  $\geq 7$



**Reference: T2013262 - Furka Plus 7064.10**

**Determination of the colour fastness to light**

Date of ending the test	03-07-2020
Standard used	ISO 105-B02 (2014)
Deviation from the standard	-
Method	1
Apparatus	Xenotest 220+ Atlas
Exposure	Constant
Irradiance	42 W/m <sup>2</sup> @ 300-400 nm
Black standard temperature	47±3°C
Effective humidity	±40%

Assessment according the blue scale standard  
Numerical rating Blue scale grade  $\geq 7$



**Reference: T2013263 - Furka Plus 7064.09**

**Determination of the colour fastness to light**

Date of ending the test	03-07-2020
Standard used	ISO 105-B02 (2014)
Deviation from the standard	-
Method	1
Apparatus	Xenotest 220+ Atlas
Exposure	Constant
Irradiance	42 W/m <sup>2</sup> @ 300-400 nm
Black standard temperature	47±3°C
Effective humidity	±40%

Assessment according the blue scale standard  
Numerical rating Blue scale grade  $\geq 7$