

Lightfastness Wallcovering 07 textile

Testing as per ISO 105 B method 2

Testresults are based upon 216 hours of exposure. Test was stopped at 216 hours.

Location test Tapetex BV, Helmond, Holland
 Testing machinery Heraeus original Hanau Xenotest 150S
 Standard blue scale 0 - 8
 Humidity 65%, Blackpanel temperature 45° Celsius
 Testing completed March 2016

<u>design</u>		<u>result</u>	<u>design</u>	<u>result</u>		
Smooth	261410 - 261411 - 261412	6	Orissa	261520 / 261524	6	
	261413	5		261525 / 261529	5	
	261414	6	Brittany	261530 / 261533	6	
	261415 - 261416	7		261534	7	
Hexagon	261420	6	261535 / 261539	6		
	261421 - 261422 - 261423	7	Relief	261540	6	
	261424	6		261541 / 261549	7	
	261425 - 261426	5	Picardy	261550 / 261556	7	
Bradford	261430 - 261431 - 261432	6		Venetia	261560 / 261563	6
	261433 - 261434	5			261564	7
	261435 - 261436	6		261565 - 261566	6	
	261437 - 261438	5	Bandol	261570 / 261576	7	
261439	6	261577 / 261579		7		
Bandra	261440	6		Evian	261580 - 261581	7
	261441	7	261582 - 261583		6	
	261442 / 261449	6	261584	7		
		Ventura	261450	6	Spira	261600 / 261606
261451 - 261452 - 261453	7		Spirit	261610		5
261454 / 261458	6			261611	6	
261459	7		261612 / 261614	5		
Decor	261460	6	Epoque	261620	5	
	261461 - 261462 - 261463	7		261621 / 261624	6	
	261464 / 261467	6	Connect	261630	6	
	261468 - 261469	7		261631	7	
Luxura	261470 - 261472	5	261632 - 261633	6		
	261473 / 261475	6	261634	5		
	261476	5	Veneto	261640	5	
Normandy	261480 / 261486	7		261641 / 261646	6	
	Crafty	261500		6	261647 / 261649	5
261501		7		Mechanica	261510 / 261519	7
261502		6				
261503		5				
261504 / 261509	6					