

Lightfastness Wallcovering 07 textile

Testing as per ISO 105 B method 2

Testresults are based upon 216 hours of exposure. Test was stopped at 216 hours.

Location test Tapetex BV, Helmond, Holland
 Testing machinery Heraeus original Hanau Xenotest 150S
 Standard blue scale 0 - 8
 Humidity 65%, Blackpanel temperature 45° Celsius
 Testing completed March 2016

<u>design</u>		<u>result</u>	<u>design</u>	<u>result</u>	
Smooth	261410 - 261411 - 261412	6	Orissa	261520 / 261524	6
	261413	5		261525 / 261529	5
	261414	6	Brittany	261530 / 261533	6
	261415 - 261416	7		261534	7
Hexagon	261420	6	Relief	261540	6
	261421 - 261422 - 261423	7		261541 / 261549	7
	261424	6	Picardy	261550 / 261556	7
	261425 - 261426	5		261560 / 261563	6
Bradford	261430 - 261431 - 261432	6	Venetia	261564	7
	261433 - 261434	5		261565 - 261566	6
	261435 - 261436	6	Bandol	261570 / 261576	7
	261437 - 261438	5		261577 / 261579	7
	261439	6		Evian	261580 - 261581
Bandra	261440	6	261582 - 261583		6
	261441	7	261584		7
	261442 / 261449	6	Spira		261600 / 261606
	Ventura	261450		6	Spirit
261451 - 261452 - 261453		7	261611	6	
261454 / 261458		6	Epoque	261612 / 261614	5
261459		7		261620	5
Decor	261460	6	Connect	261621 / 261624	6
	261461 - 261462 - 261463	7		261630	6
	261464 / 261467	6	261631	7	
	261468 - 261469	7	261632 - 261633	6	
Luxura	261470 - 261472	5	Veneto	261634	5
	261473 / 261475	6		261640	5
	261476	5	261641 / 261646	6	
Normandy	261480 / 261486	7	261647 / 261649	5	
	Crafty	261500	6	Mechanica	261510 / 261519
261501		7			
261502		6			
261503		5			
261504 / 261509		6			