

## Lightfastness Textile Wallcovering IV

### Testing as per ISO 105 B method 2

Testresults are based upon 216 hours of exposure. Test was stopped at 216 hours.

Location test

Tapetex BV, Helmond, Holland

Testing machinery

Heraeus original Hanau Xenotest 150S

Standard blue scale 0 - 8

Humidity 65%, Blackpanel temperature 45° Celsius

Testing completed

January 2014

<b>design</b>		<b>result</b>	<b>design</b>		<b>result</b>
Eternal Rondo	252000 - 252009	6	Crushed Fibres	252140 - 252149	6
Venetian Lace	252010 - 252014	6	Smeralda	252150- 252151	6
				252152	5
Venetian Lace Solid	252015 - 252019	6		252153- 252154	6
Bora	252020 - 252049	6	Smeralda Solid	252155- 252156	6
				252157	5
Pearlized Steel	252050 - 252054	6		252158 - 252159	6
Corona	252060 - 252069	6	Luxiana	252160 - 252164	6
Levante	252070 - 252074	6	Nazca	252170 - 252174	6
Levante Solid	252075 - 252079	6	Chateau Chantilly	252190 - 252194	6
Luna Mystique	252080 - 252084	6	Chateau Chantilly Solid	252195 - 252199	6
Metallic Orienta	252090 - 252-094	6	Pied de Poule	252210 - 252212	6
				252213	5
Orienta	252100 - 252119	6		252214	6
Classic Luxury	252120 - 252121	6	Pied de Poule Solid	252215 - 252217	6
	252122	5		252218	5
	252123 - 252129	6		252219	6
Botanical Engineering	252130 - 252134	6			