

Lightfastness Textile Wallcovering V

Testing as per ISO 105 B method 2

Testresults are based upon 216 hours of exposure. Test was stopped at 216 hours.

Location test

Tapetex BV, Helmond, Holland

Testing machinery

Heraeus original Hanau Xenotest 150S

Standard blue scale 0 - 8

Humidity 65%, Blackpanel temperature 45° Celsius

Testing completed

January 2014

<u>design</u>		<u>result</u>	<u>design</u>		<u>result</u>	
Golden Flax	261070	5	Linolin	261120	6	
	261071 - 261072	6		261121 - 261127	5	
	261073	5		261128 - 261129	6	
	261074	4	Irish Heritage	261130	5	
Casalin	261080	6		261131 - 261133	6	
	261081	5		261134	4	
	261082 - 261084	6	Ringolin	261135 - 261139	6	
Montalin	261090 - 261099	6		Muralin	261140 - 261149	6
	Espalin	261100		4	Mesalin	261150 - 261151
261101		6	261152 - 261159	6		
261102 - 261103		4	Artilin	261160 - 261169		6
Spica	261104	4		Linola	261170	5
Puntolin	261105 - 261109	6			261171 - 261174	6
	Linum	261110	5		Terralin	261180 - 261189
261111		6	Lin Titania	261200 - 261204		5
261112 - 261113		5				
261114		4				