

Lightfastness Textile Wallcovering V

Testing as per ISO 105 B method 2

Testresults are based upon 216 hours of exposure. Test was stopped at 216 hours.

Location test

Tapetex BV, Helmond, Holland

Testing machinery

Heraeus original Hanau Xenotest 150S

Standard blue scale 0 - 8

Humidity 65%, Blackpanel temperature 45° Celsius

Testing completed

January 2014

<u>design</u>		<u>result</u>	<u>design</u>		<u>result</u>
Golden Flax	261070	5	Linolin	261120	6
	261071 - 261072	6		261121 - 261127	5
	261073	5		261128 - 261129	6
	261074	4			
			Irish Heritage	261130	5
Casalin	261080	6		261131 - 261133	6
	261081	5		261134	4
	261082 - 261084	6			
			Ringolin	261135 - 261139	6
Montalin	261090 - 261099	6			
			Muralin	261140 - 261149	6
Espalin	261100	4			
	261101	6	Mesalin	261150 - 261151	5
	261102 - 261103	4		261152- 261159	6
Spica	261104	4	Artilin	261160 - 261169	6
Puntolin	261105 - 261109	6	Linola	261170	5
				261171 - 261174	6
Linum	261110	5			
	261111	6	Terralin	261180 - 261189	6
	261112 - 261113	5			
	261114	4	Lin Titania	261200 - 261204	5