



Textile Testing

553 76th Street · Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119



TESTING CERT. #3193.01

Report Number: 58375

Date: 05-06-2013

For the Account Of: Raxon Fabrics
2289 Ross Mill Road
Henderson, NC 27536
Contact: Connie Loftis

Client's Identification: Sindo 8027.01

Test Performed Colorfastness to Light AATCC Test Method 16-2004, Option 3

TEST DATA

Rating	Number Of Hours
Class 4.5	60

RATING SYSTEM

- Class 5 – No fading or color change
- Class 4 – Slight fading or color change
- Class 3 – Noticeable fading or color change
- Class 2 – Considerable fading or color change
- Class 1 – Much fading or color change

NOTES

Light Source: Xenon –Arc, Water Cooled, Continuous Light
Scale Used for Evaluation: AATCC Gray Scale for Color Change

ACCEPTANCE CRITERIA

A.C.T. Standard	Acceptance Criteria
Upholstery	Class 4 minimum – 40 hours
Direct Glue Wallcoverings	Class 4 minimum – 40 hours
Panels and Upholstered Walls	Class 4 minimum – 40 hours
Draperies	Class 4 minimum – 60 hours

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature: MB