

**Vescom bv
Dhr. Ron Verlouw
Postbus 70
5753 AV DEURNE
Nederland**



Your notice of
05-05-2014

Your reference

Date
10-06-2015

Analysis Report 14.02250.02

Required tests :

BS 5867-2 (2008)

Identification number	Information given by the client	Date of receipt
T1407786	Iseo	05-05-2014

Gina Créelle

Order responsible

This report runs to 3 pages and may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.

The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

VAT BE 0459.218.289

CENTEXBEL-GENT
Technologiepark 7
BE-9052 Zwijnaarde

Tel. + 32 9 220 41 51 • Fax + 32 9 220 49 55
gent@centexbel.be

Fin. Acc. 210-0472965-45

IBAN BE44 2100 4729 6545

CENTEXBEL-VERVIERS
Avenue du Parc 38
BE-4650 Herve (Chaineux)

Tel. + 32 87 32 24 30 Fax + 32 87 34 05 18
chaineux@centexbel.be

Reference: T1407786 - Iseo

Fabrics for curtains, drapes and window blinds – Flammability requirements

Date of ending the test 09-05-2014
 Standard used EN ISO 15025 (2002)
 Product standard BS 5867-2 (2008)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Flame application time (s) 5

	Afterflame time (s)	Afterglow time (s)	Flame or hole on edge	Flaming debris
Length front	0.0	0.0	no	no
Length back	0.0	0.0	no	no
Width front	0.0	0.0	no	no
Width back	0.0	0.0	no	no
Average	0.0	0.0		

Flame application time (s) 15

	Afterflame time (s)	Afterglow time (s)	Flame or hole on edge	Flaming debris
Length front	0.0	0.0	no	no
Length back	0.0	0.0	no	no
Width front	0.0	0.0	no	no
Width back	0.0	0.0	no	no
Average	0.0	0.0		

Flame application time (s) 20

	Afterflame time (s)	Afterglow time (s)	Flame or hole on edge	Flaming debris
Length front	0.0	0.0	no	no
Length back	0.0	0.0	no	no
Width front	0.0	0.0	no	no
Width back	0.0	0.0	no	no
Average	0.0	0.0		

Flame application time (s) 30

	Afterflame time (s)	Afterglow time (s)	Flame or hole on edge	Flaming debris
Length front	0.0	0.0	no	no
Length back	0.0	0.0	no	no
Width front	0.0	0.0	no	no
Width back	0.0	0.0	no	no
Average	0.0	0.0		

Type C performance requirements

The mean afterflame or afterglow times shall not exceed 2,5 s

No part of any hole nor any part of the lowest boundary of any flame shall reach the top edge or either vertical edge.

There shall be no separation of any flaming debris.

Conclusion Flammability, of the unwashed fabric, complies with the requirements of BS 5867-2:2008, type "C"