

Vescom B.V.
Sint Jozefstraat 20
5753 AV Deurne
NEDERLAND



Your notice of
06-04-2017

Your reference

Date
03-05-2017

Analysis Report 17.02145.06

Required tests :

BS 5867-2 (2008)

| Identification number | Information given by the client | Date of receipt |
|-----------------------|---------------------------------|-----------------|
| T1707713 | Syrma 8033 82g/m2 | 06-04-2017 |

Gina Créelle

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be

Inrichting erkend bij toepassing van de besluitwet van 30-01-1947 • Établissement reconnu par application de l'arrêté-loi du 30-01-1947
GENT • Technologiepark 7 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be
GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be
KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 281828 • fax +32 56 281830 • info@vkc.be
VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB

Reference: T1707713 - Syrna 8033 82g/m2

Fabrics for curtains, drapes and window blinds – Flammability requirements

Date of ending the test 02-05-2017
Standard used EN ISO 15025 (2002)
Product standard BS 5867-2 (2008)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Flame application time (s) 5

| | Afterflame time (s) | Afterglow time (s) | Flame or hole on edge | Flaming debris |
|--------------|---------------------|--------------------|-----------------------|----------------|
| Length front | 0.0 | 0.0 | no | no |
| Length back | 0.0 | 0.0 | no | no |
| Width front | 0.0 | 0.0 | no | no |
| Width back | 0.0 | 0.0 | no | no |
| Average | 0.0 | 0.0 | | |

Flame application time (s) 15

| | Afterflame time (s) | Afterglow time (s) | Flame or hole on edge | Flaming debris |
|--------------|---------------------|--------------------|-----------------------|----------------|
| Length front | 0.0 | 0.0 | no | no |
| Length back | 0.0 | 0.0 | no | no |
| Width front | 0.0 | 0.0 | no | no |
| Width back | 0.0 | 0.0 | no | no |
| Average | 0.0 | 0.0 | | |

Flame application time (s) 20

| | Afterflame time (s) | Afterglow time (s) | Flame or hole on edge | Flaming debris |
|--------------|---------------------|--------------------|-----------------------|----------------|
| Length front | 0.0 | 0.0 | no | no |
| Length back | 0.0 | 0.0 | no | no |
| Width front | 0.0 | 0.0 | no | no |
| Width back | 0.0 | 0.0 | no | no |
| Average | 0.0 | 0.0 | | |

Flame application time (s) 30

| | Afterflame time (s) | Afterglow time (s) | Flame or hole on edge | Flaming debris |
|--------------|---------------------|--------------------|-----------------------|----------------|
| Length front | 0.0 | 0.0 | no | no |
| Length back | 0.0 | 0.0 | no | no |
| Width front | 0.0 | 0.0 | no | no |
| Width back | 0.0 | 0.0 | no | no |
| Average | 0.0 | 0.0 | | |

Type C performance requirements

The mean afterflame or afterglow times shall not exceed 2,5 s

No part of any hole nor any part of the lowest boundary of any flame shall reach the top edge or either vertical edge.

There shall be no separation of any flaming debris.

Conclusion Flammability, of the unwashed fabric, complies with the requirements of BS 5867-2:2008, type "C"