

Vescom BV  
St. Jozefstraat 20  
5750 AH Deurne



Your notice of  
27-02-2017

Your reference

Date  
17-03-2017

## Analysis Report 17.01222.04

Required tests :

**DIN 4102-1B2 (1998)**

**Burning behaviour - B2**

Identification number	Information given by the client	Date of receipt
T1704509	ZANZIBAR	27-02-2017

Gina Créelle

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

**CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be**

Inrichting erkend bij toepassing van de besluitwet van 30-01-1947 • Établissement reconnu par application de l'arrêté-loi du 30-01-1947  
GENT • Technologiepark 7 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be  
GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be  
KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 281828 • fax +32 56 281830 • info@vkc.be  
VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB

Reference: T1704509 - ZANZIBAR

**Burning behaviour - B2**

Date of ending the test 16-03-2017  
Standard used DIN 4102-1B2 (1998)

Deviation from the standard -

Conditioning 23°C, relative humidity 50%

Ignition Surface - front

Length

	1	2	3	4	5
Time to reach 150 mm mark (s) °	*	*	*	*	*
Ignition filter paper within 20 s after flame application	no	no	no	no	no

° tip of the flame

\* = time to reach the mark > 20 s or mark not reached

Width

	1	2	3	4	5
Time to reach 150 mm mark (s) °	*	*	*	*	*
Ignition filter paper within 20 s after flame application	no	no	no	no	no

° tip of the flame

\* = time to reach the mark > 20 s or mark not reached

Criteria

- time to reach the mark > 20 s for all test specimens

**Conclusion B2**