



VESCOM BV
P.O. Box 70
NL-5753 AV DEURNE
NEDERLAND

your e-mail of
2003-07-28

your reference

our reference
PVH/5106

date
Zwijnaarde, 2009-06-02

Analysis Report 35949/I

Modification of analysis report 35949, made on 2003-08-19

Required tests :

DIN 4102 part 1 - 1998 : Test in accordance with § 6.2 - B2 classification

Sampling by : Schellens Furnishing Textiles bv

Identification number	Information given by the client	Date of receipt
T307285	Zanzibar velours - mohair	2003-07-28

Pros Van Hoeyland
order responsible

For further information, please contact our sectorial adviser Pros Van Hoeyland

This report runs to 2 pages and may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.

ISO 17025



071-T

VAT BE 459 218 289
CENTEXBEL-GENT
Technologiepark 7
BE-9052 Zwijnaarde
Tel. + 32 9 220 41 51 • Fax + 32 9 220 49 55
e-mail gent@centexbel.be

Fin. Acc. 210-0472965-45

IBAN BE44 2100 4729 6545

CENTEXBEL-BRUSSELS
Montoyerstraat 24 B2
BE-1000 Brussels

Tel. + 32 2 287 08 30 • Fax + 32 2 230 68 15

www.centexbel.be

Reference : T307285 – Zanzibar velours - mohair

DIN 4102 part 1 - 1998 : Test in accordance with § 6.2 - B2 classification

End of tests: 19 August 2003

The tests are carried out in accordance with DIN 4102(B2) - surface ignition.

orientation test specimen : vertical
flame height : 20 mm
burner : <45°
flame application time : 15 s

Surface ignition

Length

test specimen	1	2	3	4	5
150 mm mark reached within (s)	I	I	I	I	I
ignition filter paper within 20 s after flame application	no	no	no	no	no

Width

test specimen	1	2	3	4	5
150 mm mark reached within (s)	I	I	I	I	I
ignition filter paper within 20 s after flame application	no	no	no	no	no

I = mark not reached within 20 s after flame application

Criteria

time to reach the mark : >20 s for all test specimens

Conclusion : B2