

## TEST REPORT

**Applicant:** Raxon / Vescom  
261 Fifth Avenue Rm 2301  
New York, NY 10010  
**Attention:** Christine Wekilsky  
**E-Mail:** cwekilsky@raxon.com

**Sample Description as Declared :**

Description : Balta Solid Upholstery  
Style# : 7040.01  
No. Of Samples: 1  
End Use : Upholstery  
Color : Beige  
Fabric Weight : 14 oz/yd  
Fiber Content : 80% Wool, 20% Polyamide  
Date Received / Date Test Started : August 22, 2016 / September 2, 2016



For and on behalf of  
Intertek Products Group North America :



**Duraisamy Ravichandran**  
Operations Manager  
Softlines Testing Laboratories



**TEST RESULTS:**

**BREAKING STRENGTH**

ASTM D 5034

Average(lbf)

Warp 192.3  
Fill 163.7

**SEAM STRENGTH**

ASTM D4034-92

| Average(lbf) | SEAM OPENED AT<br>¼"/6MM | SEAM<br>STRENGTH | TYPE OF SEAM<br>RUPTURE |
|--------------|--------------------------|------------------|-------------------------|
| Warp         | *                        | 92.1             | STB                     |
| Fill         | *                        | 82.1             | STB                     |

REMARK: STB = SEWING THREAD BREAK  
\* = THE SEAM OPENING WAS LESS THAN ¼INCH/6MM THOUGH THE ULTIMATE SEAM STRENGTH WAS FOUND AS STATED

**ABRASION RESISTANCE ( OSCILLATORY CYLINDER METHOD)**

ASTM D 4157

Abradent Used: #10 Cotton Duck  
Cycles Requested: 100,000

|          |                                |                                |
|----------|--------------------------------|--------------------------------|
|          | Warp/Wales                     | Fill/ Courses                  |
| Average: | No wear at 100,000 double rubs | No wear at 100,000 double rubs |

The end point is reached on a woven fabric when two or more yarns have broken or on a knitted fabric when a hole appears.





**RESISTANCE TO PILLING AS RECEIVED: BRUSH PILLING TESTER**

ASTM D 3511

Running Time:

Average 4.0

**RATING SYSTEM**

- Grade 5, No Pilling
- Grade 4, Slight Pilling
- Grade 3, Moderate Pilling
- Grade 2, Severe Pilling
- Grade 1, Very Severe Pilling

**COLORFASTNESS TO CROCKING**

AATCC 8

|     |     |
|-----|-----|
| Dry | 4.5 |
| Wet | 4.5 |

**COLORFASTNESS TO LIGHT**

AATCC 16.3, Option 3

|                       |     |
|-----------------------|-----|
| Color Change @ 40 AFU | 4.5 |
|-----------------------|-----|

**RATING SYSTEM**

- Grade 5, Negligible Color Change/Staining
- Grade 4, Slight Color Change/Staining
- Grade 3, Noticeable Color Change/Staining
- Grade 2, Considerable Color Change/Staining
- Grade 1, Excessive Color Change/Staining

**Intertek Consumer Goods**

545 E Algonquin Road, Suite F,  
Arlington Heights, Illinois 60005  
Telephone: 847-871-1020 Fax: 847-439-6156



AT-1348

**CA TB 117:2013 – Smolder Resistance of Materials used in Upholstered Furniture**

*-Section 1: Cover Fabric Test*

The cover fabric material submitted **does meet** the flame resistance requirements when tested in accordance with the Bureau of Electronic & Appliance Repair Home Furnishings and Thermal Insulation, Technical Bulletin 117 – 2013, Section 1: Cover fabric test

| Component Description: Beige Fabric |                               |  |   |
|-------------------------------------|-------------------------------|--|---|
| Initial Test                        |                               |  |   |
|                                     | Vertical Char length (Inches) | Mock-up specimen continues to smolder After 45 Minutes | Mock-up test specimen transitions to open flaming |
| Specimen 1                          | 0.4                           | No   | No  |
| Specimen 2                          | 0.6                           | No   | No  |
| Specimen 3                          | 0.5                           | No   | No  |

**Requirements: A cover fabric material considered pass or fail based on following criteria**

1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
  - a). The mock-up test specimen continues to smolder after 45 minutes test duration.
  - b). A vertical Char length (measured as specified in step 11.9 of ASTM E1353-08a<sup>ε1</sup>) of more than 1.8 inches (45 mm) develops on the cover fabric.
  - c). The mock-up test specimen transitions to open flaming.
2. The cover fabric passes the test if three initial mock-up specimens pass the test, i.e., the cigarettes burn their full length and the mock-ups are no longer smoldering.
3. If more than one initial specimen fails, the cover fabric fails the test.
4. If any one of the three initial specimens fails, repeat the test on additional three specimens.
5. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test.

**Note:** For Cover fabrics that pass this section, the first layer of filling materials located below the cover fabric shall also meet the test requirements of section 3 of CA TB -117 :2013

**Intertek Consumer Goods**

545 E Algonquin Road, Suite F,  
 Arlington Heights, Illinois 60005  
 Telephone: 847-871-1020 Fax: 847-439-6156



AT-1348



*The test results stated in this report relate only to the item(s) tested. This test report may not be reproduced except in full, without written approval of Intertek.*

---

*If you need assistance in interpreting these results or if you have any questions, please feel free to call  
Customer Service Department*

*This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.*

**Intertek Consumer Goods**

545 E Algonquin Road, Suite F,  
Arlington Heights, Illinois 60005  
Telephone: 847-871-1020 Fax: 847-439-6156



TESTING LABORATORY  
AT-1348