

TEST REPORT

Applicant: Raxon / Vescom
261 Fifth Avenue Rm 2301
New York, NY 10010
Attention: Christine Wekilsky
E-Mail: cwekilsky@raxon.com

Sample Description as Declared :

Description : Balta Solid Upholstery
Style# : 7040.01
No. Of Samples: 1
End Use : Upholstery
Color : Beige
Fabric Weight : 14 oz/yd
Fiber Content : 80% Wool, 20% Polyamide
Date Received / Date Test Started : August 22, 2016 / September 2, 2016



For and on behalf of
Intertek Products Group North America :



Duraisamy Ravichandran
Operations Manager
Softlines Testing Laboratories



RESISTANCE TO PILLING AS RECEIVED: BRUSH PILLING TESTER

ASTM D 3511

Running Time:

Average 4.0

RATING SYSTEM

- Grade 5, No Pilling
- Grade 4, Slight Pilling
- Grade 3, Moderate Pilling
- Grade 2, Severe Pilling
- Grade 1, Very Severe Pilling

COLORFASTNESS TO CROCKING

AATCC 8

Dry	4.5
Wet	4.5

COLORFASTNESS TO LIGHT

AATCC 16.3, Option 3

Color Change @ 40 AFU	4.5
-----------------------	-----

RATING SYSTEM

- Grade 5, Negligible Color Change/Staining
- Grade 4, Slight Color Change/Staining
- Grade 3, Noticeable Color Change/Staining
- Grade 2, Considerable Color Change/Staining
- Grade 1, Excessive Color Change/Staining

Intertek Consumer Goods

545 E Algonquin Road, Suite F,
Arlington Heights, Illinois 60005
Telephone: 847-871-1020 Fax: 847-439-6156



AT-1348

CA TB 117:2013 – Smolder Resistance of Materials used in Upholstered Furniture
 -Section 1: Cover Fabric Test

The cover fabric material submitted **does meet** the flame resistance requirements when tested in accordance with the Bureau of Electronic & Appliance Repair Home Furnishings and Thermal Insulation, Technical Bulletin 117 – 2013, Section 1: Cover fabric test

Component Description: Beige Fabric			
Initial Test			
	Vertical Char length (Inches)	Mock-up specimen continues to smolder After 45 Minutes	Mock-up test specimen transitions to open flaming
Specimen 1	0.4	No	No
Specimen 2	0.6	No	No
Specimen 3	0.5	No	No

Requirements: A cover fabric material considered pass or fail based on following criteria

1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
 - a). The mock-up test specimen continues to smolder after 45 minutes test duration.
 - b). A vertical Char length (measured as specified in step 11.9 of ASTM E1353-08a^{ε1}) of more than 1.8 inches (45 mm) develops on the cover fabric.
 - c). The mock-up test specimen transitions to open flaming.
2. The cover fabric passes the test if three initial mock-up specimens pass the test, i.e., the cigarettes burn their full length and the mock-ups are no longer smoldering.
3. If more than one initial specimen fails, the cover fabric fails the test.
4. If any one of the three initial specimens fails, repeat the test on additional three specimens.
5. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test.

Note: For Cover fabrics that pass this section, the first layer of filling materials located below the cover fabric shall also meet the test requirements of section 3 of CA TB -117 :2013



The test results stated in this report relate only to the item(s) tested. This test report may not be reproduced except in full, without written approval of Intertek.

*If you need assistance in interpreting these results or if you have any questions, please feel free to call
Customer Service Department*

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.

Intertek Consumer Goods

545 E Algonquin Road, Suite F,
Arlington Heights, Illinois 60005
Telephone: 847-871-1020 Fax: 847-439-6156



TESTING LABORATORY
AT-1348