

**Ir. Ron Verlouw
VESCOB BV
Postbus 70
NL-5753 AV DEURNE
NEDERLAND**

your delivery of
2010-07-26

your reference

our reference
PVH/7349

date
Zwijnaarde, 2010-08-02

Analysis Report 75602/C

Required tests :

**BS 5852: 2006, clause 11 (upholstery composite)
Assessment of the ignitability of upholstered seating - crib ignition source no. 5**

Identification number	Information given by the client	Date of receipt
T008351	Vescom Vinyl Upholstery	2010-07-26

Pros Van Hoeyland
order responsible

For further information, please contact our sectorial adviser Pros Van Hoeyland

This report runs to 2 pages and may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.

ISO 17025



VAT BE 0459.218.289
CENTEXBEL - GENT
Technologiepark 7
BE-9052 Zwijnaarde
Tel. + 32 9 220 41 51 • Fax + 32 9 220 49 55
e-mail gent@centexbel.be

Fin. Acc. 210-0472965-45

IBAN BE44 2100 4729 6545

CENTEXBEL - BRUSSELS
Montoyerstraat 24 B2
BE-1000 Brussels
Tel. + 32 2 287 08 30 • Fax + 32 2 230 68 15

our reference	date	page
PVH/7349	2010-08-02	2 / 2

Reference : T008351 - Vescom Vinyl Upholstery

BS 5852: 2006, clause 11 (upholstery composite)
Assessment of the ignitability of upholstered seating - crib ignition source no. 5

The following test results relate only to the ignitability of the combination of upholstery composites (BS 5852:2006, clause 11) under the particular conditions of test stated ; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

End of tests: 2 August 2010

A. Materials tested

Cover	:	- quality	Vescom Vinyl Upholstery
		- water soaking	/
Filling	:	- quality	F 35140 (Recticel) *
		- density	fire retardant foam ± 35 kg/m ³

* The filling complies with schedule 1 part 1 of the UK Furniture and Furnishings (Fire) (Safety) Regulations 1988

B. Test results - ignition source crib 5

	<u>test 1</u>	<u>test2</u>
<u>Flaming criteria</u>		
- unsafe escalating combustion	no	no
- test assembly consumed	no	no
- flames to extremities	no	no
- flames through thickness	no	no
- flame time >10 min	no	no
flame time	4 min 22 s	3 min 55 s
<u>Smouldering criteria</u>		
- unsafe escalating combustion	no	no
- test assembly consumed	no	no
- smoulders to extremities	no	no
- smoulders through thickness	no	no
- smoke/heat/glowing more than 60 min	no	no
- smoulders more than 100 mm from source	no	no
	non-ignition	non-ignition

Conclusion: non-ignition - NI/5